NANOPARTICLES IN SCAFFOLD TISSUE ENGINEERING: DESIGN, FUNCTIONALITY, AND BIOMEDICAL APPLICATIONS

A Dissertation
Submitted in partial fulfilment of the requirement for the degree of

MASTER OF SCIENCE
in
BIOTECHNOLOGY

by:
Asiya Perween
24/MSCBIO/62
Under the supervision of
Prof. Prakash Chandra

Department of Biotechnology
DELHI TECHNOLOGICAL UNIVERSITY
(Formerly Delhi College of Engineering)
Shahbad Daulatpur, Bawana Road, Delhi-110042. India
May, 2026

ACKNOWLEDGEMENTS

First and foremost, I would like to express my deepest and most sincere gratitude to my supervisor, Prof. Prakash Chandra , for his invaluable guidance, unwavering support, and scholarly expertise throughout the course of this research. Their constructive feedback, intellectual encouragement, and dedication to academic excellence have been instrumental in shaping both this thesis and my growth as a researcher. I am truly grateful for the time, patience, and wisdom he has generously invested in my academic journey.

My sincere appreciation goes to the faculty and staff of the Department of Biotechnology Delhi Technological University, for providing an intellectually stimulating and supportive academic environment. Access to the university's research facilities, library resources, and scientific databases was indispensable to the completion of this work.

I am deeply grateful to my fellow researchers and colleagues for the stimulating scientific discussions, collaborative spirit, and moral support they provided throughout this journey. The shared experiences, ideas, and encouragement exchanged within our research community made this endeavour both enriching and rewarding.

A special acknowledgement is due to the researchers, scientists, and scholars whose published work forms the scientific foundation of this thesis. The body of knowledge they have collectively contributed to the fields of nanotechnology, biomaterials science, and tissue engineering has been the intellectual bedrock upon which this work is built.

On a personal note, I owe an immeasurable debt of gratitude to my family particularly my parents for their unconditional love, endless patience, and unwavering belief in my abilities throughout my academic journey. Their sacrifices, encouragement, and constant motivation have been my greatest source of strength and inspiration. No words can adequately express the depth of my appreciation for everything they have done.

Finally, I give thanks to God for the strength, clarity of mind, and perseverance to complete this work. Every opportunity and ability I possess is a blessing for which I am profoundly grateful.

ASIYA PERWEEN

24/MSCBIO/62

DELHI TECHNOLOGICAL UNIVERSITY
(Formerly Delhi College of Engineering)
Shahbad Daulatpur, Bawana Road, Delhi-110042

DECLARATION

I, ASIYA PERWEEN 24/MSCBIO/62 hereby declare that the work presented in the dissertation entitled "Nanoparticles in Scaffold Tissue Engineering: Design, Functionality, and Biomedical Applications" submitted in partial fulfilment of the requirements for the award of the Degree of Master of Science in Biotechnology to the Department of Biotechnology, Delhi Technological University , is an authentic record of my own work carried out during the academic session 2024 to 2026 under the supervision of Prof. Prakash Chandra.

The matter presented in this dissertation has not been submitted by me for the award of any other degree or diploma of this or any other institution/university.

Candidate's Signature

DELHI TECHNOLOGICAL UNIVERSITY

(Formerly Delhi College of Engineering)
Shahbad Daulatpur, Bawana Road, Delhi-110042

CERTIFICATE BY THE SUPERVISOR

This is to certify that the Dissertation Project entitled **"Nanoparticles in Scaffold Tissue Engineering: Design, Functionality, and Biomedical Applications"** submitted by Asiya Perween (24/MSCBIO/62), Department of Biotechnology, Delhi Technological University, Delhi, in partial fulfilment of the requirement for the award of the degree of Master of Science in Biotechnology, is a record of the work carried out by the student under my supervision. To the best of my knowledge, this work has not been submitted in part or full for any Degree or Diploma to this University or elsewhere.

Date: _____

Prof. Prakash Chandra
Supervisor
Department of Biotechnology
Delhi Technological University

Prof. Yasha Hasija
Head of Department
Department of Biotechnology
Delhi Technological University

"NANOPARTICLES IN SCAFFOLD TISSUE ENGINEERING: DESIGN, FUNCTIONALITY, AND BIOMEDICAL APPLICATIONS"

ASIYA PERWEEN

24/MSCBIO/62

ABSTRACT

Tissue engineering has emerged as a transformative field in regenerative medicine, seeking to restore or replace damaged tissues and organs through the synergistic combination of biomaterial scaffolds, cells, and bioactive signals. Despite significant advances, conventional scaffolds often fall short in replicating the complex biochemical and biophysical cues of the native extracellular matrix, limiting their therapeutic efficacy. The integration of nanoparticles into scaffold systems has opened new frontiers in addressing these limitations, offering unprecedented control over scaffold architecture, mechanical properties, and biological functionality at the nanoscale. This thesis investigates the multifaceted roles of nanoparticles in scaffold-based tissue engineering, encompassing their design principles, functional contributions, and translational potential. A broad spectrum of nanoparticle types is examined, including metallic, polymeric, ceramic, and carbon-based nanomaterials, each offering distinct physicochemical properties that can be tailored to specific tissue engineering applications. The mechanisms by which nanoparticles enhance scaffold performance are explored in detail, including mechanical reinforcement, controlled and stimuli-responsive delivery of drugs and growth factors, electrical and magnetic stimulation of cell behavior, and inherent antibacterial activity. Tissue-specific applications are critically reviewed across bone, cartilage, neural, cardiac, and dermal systems, highlighting how nanoparticle–scaffold composites promote targeted cellular responses such as osteogenesis, chondrogenesis, neurogenesis, and angiogenesis. Particular attention is given to biocompatibility and nanotoxicology, with a thorough assessment of cytotoxicity mechanisms, inflammatory responses, and current regulatory considerations governing the clinical use of nano-enabled biomaterials. Finally, the thesis addresses persistent challenges in the field, including scalability of fabrication, long-term biodegradation behavior, vascularization of engineered constructs, and the gap between laboratory findings and clinical translation. Emerging directions such as 4D bioprinting, AI-assisted scaffold design, and personalized nano-scaffold platforms are discussed as promising avenues for the next generation of tissue engineering solutions. Collectively, this work underscores the pivotal role of nanoparticle integration in advancing scaffold tissue engineering toward clinically viable regenerative therapies.

Keywords: nanoparticles, scaffold, tissue engineering, regenerative medicine, extracellular matrix, drug delivery, biocompatibility, nanotoxicology, biomaterials

List of Publications

1. Conference Paper

Asiya Perween, Nishika Sharma and Prakash Chandra, “Review: Nanoparticle Applications in Scaffold-Based Tissue Engineering,” presented at the International Conference on Bioinformatics Applications in Biomedical Innovations (ICBABI-26) organized by the National Institute for Engineering and Research (NIER), Coimbatore, India, on 16th May 2026.

2. Poster Presentation

Asiya Perween, “Lipid Nanoparticles as Key Delivery Vehicles for mRNA Vaccines,” Biodiverse Poster Presentation, held on 28th April 2026 and presented scientific contributions related to biotechnology and biomedical.

TABLE OF CONTENTS

Title	Page No.
Acknowledgements	ii
Declaration	iii
Certificate	vi
Abstract	v
List of publication	vi
Table of content	vii - viii
List of Figures	ix
List of tables	x
List of Symbols and Abbreviations	xi

Chapter 1: Introduction

1.1 Background and Motivation 1

1.2 The Tissue Engineering Paradigm: Cells, Scaffolds, and Signals 1

1.3 Limitations of Conventional Scaffolds 1-2

1.4 Emergence of Nanotechnology in Regenerative Medicine 2

1.5 Thesis Objectives and Scope 3

Chapter 2: Literature Review

2.1 Scaffold Fundamentals 4-18

2.2 Nanoparticle Classification and Properties 18-30

2.3 Nanoparticle–Scaffold Integration Strategies 30-31

2.4 Biological Interactions 32-33

Chapter 3: Functional Roles of Nanoparticles in Scaffolds

3.1 Mechanical Reinforcement 34

3.2 Controlled Drug and Growth Factor Delivery 34

3.3 Electrical and Magnetic Stimulation 35-36

3.4 Antibacterial Properties 36-37

3.5 Imaging and Diagnostics 37-38

Chapter 4: Tissue-Specific Applications

4.1 Bone Tissue Engineering 39

4.2 Cartilage Tissue Engineering 39-40

4.3 Neural Tissue Engineering 40-41

4.4 Cardiac Tissue Engineering 41

4.5 Skin and Wound Healing 42

Chapter 5: Biocompatibility, Toxicity, and Safety Considerations

5.1 Cytotoxicity Mechanisms of Nanoparticles 43

5.2 Oxidative Stress and Inflammatory Responses 43-44

5.3 In Vitro vs. In Vivo Safety Assessment 44

5.4 Regulatory Frameworks: FDA and EMA Perspectives 44

5.5 Strategies to Mitigate Nanotoxicity 45

Chapter 6: Challenges and Future Directions

6.1 Scalability and Manufacturing Limitations 46

6.2 Long-Term Biodegradation and Clearance 46-47

6.3 Vascularization of Thick Scaffolds 47

6.4 Emerging Trends 48

Chapter 7: Conclusion

7.1 Summary of Major Findings 49

7.2 Future Perspectives 49

References 50-56

LIST OF FIGURES

S.NO.	TITLE OF FIGURE	PAGE NUMBER
1	various biological features of an ideal scaffold for tissue engineering.	4
2	Different types of scaffolds sterilization representations.	5
3	Mechanical properties of scaffolds important for biomedical applications.	6
4	Various methods of creating an ideal scaffold for biomedical applications.	9
5	Diagram of Solvent Casting and Particulate Leaching Technique.	14
6	Schematic representation of gas foaming process.	14
7	Schematic Illustration of an Electrospinning Setup for Scaffold Fabrication	15
8	Schematic representation of stereolithography technique.	16
9	Schematic Representation of Fused Deposition Modeling Technique	16
10	Schematic representation of selective laser sintering technique.	17
11	Illustrates the different types of Bioceramics	19
12	Various carbon allotropes at the nanoscale, categorized into 0D, 1D, 2D, and 3D nanostructural forms	23

LIST OF TABLES

S.NO.	TITLE OF TABLE	PAGE NUMBER
1	Summary of ceramic materials used for making scaffolds.	7
2	Classification of conventional methods used for scaffold fabrication.	9
3	various additive manufacturing techniques used for scaffold fabrication	12
4	Carbon nanomaterials and their applications.	25

LIST OF ABBREVIATIONS

1. ECM: Extracellular matrix
2. iPSs: induced pluripotent stem cells
3. BMP-2 :Bone Morphogenetic Protein-2
4. VEGF :Vascular Endothelial Growth Factor
5. TGF: Transforming Growth Factor-beta
6. HA: hydroxyapatite
7. TCP: tricalcium phosphate
8. TIPS: Thermal Induced Phase Separation
9. GF :GAs foaming
10. SLA: stereolithography
11. FDM: Fused Deposition Modeling
12. SLS: Selective Laser Sintering
13. LAB: Laser Assisted Bioprinting
14. SLM : Selective Laser Melting
15. EBM: Electron Beam Melting
16. DED: Direct Energy Deposition
17. DMLS: Direct Material Laser Sintering
18. MBG: Mesoporous Bioactive Glass
19. NGGs: Nanobioactive Glasses
20. NPs : Nanoparticles
21. PLA: Poly(lactic acid) or Polylactide
22. PLGA: Poly(lactic-co-glycolic acid)
23. PCL: Polycaprolactone
24. PEG: Polyethylene glycol
25. SCI : Spinal Cord Injury
26. GFAP: Glial Fibrillary Acidic Protein
27. BDNF: Brain-Derived Neurotrophic Factor
28. MI: Myocardial infraction
29. GO: Graphene Oxide
30. VEGF: Vascular Endothelial Growth Factor
31. HGF: Hepatocyte Growth Factor
32. IGF: Insulin-like Growth
33. Wnt: Wingless-related integration site.

CHAPTER 1

INTRODUCTION

1.1 Background and Motivation

The loss or failure of tissues and organs resulting from disease, trauma, and congenital defects represents one of the most pressing challenges in modern medicine. Musculoskeletal conditions alone affect more than 1.71 billion people globally, while cardiovascular diseases remain the leading cause of mortality worldwide (WHO, 2021). Conventional treatments including autografts, allografts, and synthetic prosthetics carry significant limitations donor site morbidity, immune rejection, disease transmission, and biological integration failure creating an urgent need for biomaterial-based regenerative alternatives (Langer & Vacanti, 1993).

Conventional scaffold systems fail to adequately replicate the nanoscale architectural and biochemical complexity of native extracellular matrix, cannot sustain adequate vascularization of thick constructs, and offer limited spatiotemporal control over bioactive signal delivery (Hollister, 2005; Place et al., 2009). These fundamental inadequacies drive the need for nanotechnology-based scaffold strategies capable of addressing multiple scaffold requirements simultaneously.

1.2 The Tissue Engineering Paradigm

Tissue engineering is founded upon the coordinated interplay of three components: cells, scaffolds, and bioactive signals the "tissue engineering triad" (Langer & Vacanti, 1993). Cells provide the biological machinery for tissue synthesis; scaffolds provide structural support mimicking native ECM; and bioactive signals including growth factors, mechanical cues, and electrical stimuli direct cell behavior toward tissue-specific outcomes (O'Brien, 2011).

Cells- employed include autologous cells, allogeneic cells, mesenchymal stem cells (MSCs), and induced pluripotent stem cells (iPSCs) — each offering distinct advantages regarding availability, immunocompatibility, and differentiation potential (Pittenger et al., 1999; Takahashi & Yamanaka, 2006).

Scaffolds- must satisfy requirements of biocompatibility, biodegradability, mechanical integrity, porosity, and biomimetic surface chemistry. Fabrication techniques include electrospinning, freeze-drying, and 3D bioprinting (Murphy & Atala, 2014).

Bioactive signals- encompass growth factors including BMP-2, VEGF, and TGF-β; mechanical stimuli transduced through mechanosensitive pathways; and electrical signals essential for electroactive tissues including cardiac muscle and neural tissue (Engler et al., 2006; Ferrara et al., 2003).

1.3 Limitations of Conventional Scaffolds

Despite significant progress, conventional scaffolds face five interconnected limitations:

Mechanical insufficiency: Natural polymer scaffolds exhibit compressive moduli orders of magnitude below native bone and cartilage. The inverse relationship between porosity and mechanical strength creates a fundamental design dilemma that conventional materials cannot resolve (Karageorgiou & Kaplan, 2005).

Inadequate ECM mimicry: Synthetic polymers lack the nanoscale fibrillar architecture, bioactive surface chemistry, and dynamic biochemical environment of native ECM, resulting in poor cell adhesion, aberrant morphology, and impaired differentiation (Ma, 2008).

Vascularization failure: Cells beyond 200 μm from a capillary experience fatal hypoxia and nutrient deprivation. Host vascular ingrowth proceeds at only 1–5 μm per hour — insufficient to rescue cells in thick construct interiors (Roukema et al., 2008).

Limited signal delivery control: Conventional scaffold drug delivery produces burst release pharmacokinetics that deplete growth factor reserves prematurely, failing to replicate the sustained spatiotemporal signaling dynamics of native ECM (Chen & Mooney, 2003).

Fabrication constraints: Conventional techniques produce scaffolds with random pore architectures, limited reproducibility, and inadequate scalability for patient-specific clinical deployment (Hutmacher, 2000).

1.4 Emergence of Nanotechnology in Regenerative Medicine

Nanotechnology the science of manipulating matter at 1–100 nm dimensions has emerged as a transformative enabling technology for regenerative medicine, introducing qualitatively new functional capabilities that address scaffold limitations at their most fundamental level (Dvir et al., 2011; Whitesides, 2003). The intellectual foundations were established by Feynman's 1959 vision of atomic-scale manipulation, formalized as "nanotechnology" by Taniguchi in 1974, and translated into medical applications through pioneering work in nanoparticle synthesis and self-assembling biomaterials in the 1990s (Feynman, 1960; Hartgerink et al., 2001). The FDA approval of Doxil in 1995 marked the first clinical translation of a nanoscale drug delivery system, establishing regulatory precedent for nanoparticle-based medical products (Bobo et al., 2016).

At the nanoscale, materials exhibit unique properties exceptionally high surface area-to-volume ratios, quantum mechanical effects, tunable optical and magnetic behaviours that are not observed in bulk materials and that are directly exploitable for tissue engineering (Nel et al., 2009). Nanoparticle incorporation enables mechanical reinforcement of scaffold matrices, sustained growth factor delivery, electrical conductivity for electroactive tissues, antibacterial protection, and real-time bioimaging within a single integrated scaffold platform (Shi et al., 2010).

The recognition that nanoscale substrate stiffness, topography, and ligand spacing directly determine stem cell fate through mechanotransduction pathways established nanoscale material engineering as a fundamental requirement of regenerative scaffold design rather than an optional enhancement (Engler et al., 2006; Dalby et al., 2007).

1.5 Thesis Objectives and Scope

The primary aim of this thesis is to comprehensively investigate nanoparticle integration into biomaterial scaffolds for tissue engineering, focusing on how nanoscale design strategies enhance scaffold functionality and advance regenerative medicine outcomes.

Specific objectives are:

1. To classify and characterize nanoparticle types used in scaffold tissue engineering

2. To examine nanoparticle–scaffold integration strategies and their effects on scaffold properties

3. To evaluate functional roles of nanoparticles in enhancing scaffold performance

4. To review tissue-specific applications across bone, cartilage, neural, cardiac, and skin systems

5. To evaluate biocompatibility, cytotoxicity, and safety profiles of nanoparticle–scaffold systems

6. To identify challenges and propose future directions for clinical translation

Scope inclusions: Nanoparticles with at least one dimension of 1–100 nm integrated into scaffold; natural and synthetic biomaterials; in vitro and in vivo peer-reviewed studies from the past two decades; five primary tissue systems; functional properties.

Scope exclusions: Standalone nanoparticle drug delivery systems not integrated into scaffolds; two-dimensional culture substrates; clinical trial data; organ-on-chip platforms.

Significance

This thesis highlights the increasing importance of nanotechnology in the field of tissue engineering. By combining information on different nanoparticles, scaffold systems, and tissue applications, it provides a useful reference for researchers and helps guide the development of advanced biomaterials for future regenerative therapies.

CHAPTER 2

LITERATURE REVIEW

SCAFFOLD FUNDAMENTALS

2.1 Characteristics of ideal scaffold

The characteristics that a scaffold should have depend on the type of tissue that needs to be repaired. For instance, when dealing with harder tissues like bone, rigid scaffolds are necessary, whereas for softer tissues such as nerves, skin, and blood vessels, flexible or soft scaffolds can be used. The properties of the scaffold vary depending on the tissue to support proper cell growth and function. For example, harder scaffolds work well with mesenchymal stem cells, while softer ones are more suitable for neural cells. Scaffolds used for specialized tissues, like heart valves, need to be strong enough to handle blood flow and pressure, and also prevent issues like clotting and calcification. Controlling how the scaffold breaks down over time is also important, along with ensuring it is biocompatible and strong enough for bone repair.

2.1.1 Biological Properties

For a scaffold to work effectively, it must be biocompatible and non-toxic, allowing new tissues to grow without damaging surrounding tissues. It should closely resemble the natural extracellular matrix (ECM) and provide a suitable environment for cells to attach, grow, and differentiate. The surface of the scaffold plays a key role in how cells attach and interact with it. Generally, surfaces that are hydrophilic (water-attracting) are better for cell growth, while hydrophobic (water-repelling) surfaces are not as effective. Also, the size of the pores and the overall porosity of the scaffold affect how cells move, receive nutrients, and get oxygen. Well-designed larger pores encourage tissue growth, while poorly designed smaller pores may not allow cells to fully grow and spread.



Fig. 1. various biological features of an ideal scaffold for tissue engineering.

2.1.2 Biodegradability and Sterilizability

A scaffold should also gradually take on the role of the body's own extracellular matrix (ECM) as new tissue forms and eventually be replaced by the body's own ECM. The byproducts of its breakdown should be safe and not harmful to surrounding tissues. It is important to manage the breakdown process so that it supports proper tissue regeneration. Another key feature is its ability to be sterilized, since scaffolds must be free from contamination before they are implanted. There are several ways to sterilize scaffolds, such as using chemicals, radiation, or plasma treatments. However, some methods might change the scaffold's properties, so it is important to choose a method that is effective without damaging the scaffold's structure. Different sterilization techniques for scaffolds are shown in Fig. 2.



Fig. 2. Different types of scaffolds sterilization representations.

2.1.3 Mechanical Properties

For certain structures and functions needed in tissue engineering, a scaffold needs to meet specific requirements. Mechanical properties such as strength, stiffness, and elasticity are important because the scaffold must help the tissue function during healing. These properties should closely match those of the tissue it is meant to support. For example, bone scaffolds need to be strong to bear body weight, while skin scaffolds should be flexible and elastic, similar to skin. One challenge is maintaining mechanical strength while allowing enough porosity for cell growth and movement, which can make the scaffold unstable. Natural materials are usually good at being biocompatible but not as good in terms of mechanical strength, while synthetic materials offer good mechanical properties but may not be as biocompatible. These limitations can be reduced by using a mix of natural and synthetic materials in scaffolds to improve overall performance.



Fig. 3. Mechanical properties of scaffolds important for biomedical applications.

2.1.4 Materials used for scaffold fabrication

The properties of a scaffold can vary widely based on the materials used and the methods of fabrication. The choice of material is very important as it affects the scaffold's structure, strength, surface features, biodegradability, and performance in tissue engineering. Materials such as polymers, ceramics, glasses, metals, alloys, and composites are commonly used to make scaffolds.

a. Polymers - Polymers are frequently used in scaffold creation because they offer excellent biocompatibility, biodegradability, high porosity, and suitable mechanical properties.

They can also mimic the natural extracellular matrix (ECM), which supports cell growth.

There are two main types of polymers:

i. Natural polymers such as collagen, gelatin, chitosan, silk, and cellulose.

These materials provide good support for biological functions and make it easier for tissues to adhere, grow, and repair. However, they often lack sufficient strength, have low stability, and can be difficult to keep free from contamination.

ii. Artificial polymers like PLA, PLGA, PCL, and PEG. These materials offer improved mechanical strength, controlled breakdown, and are easy to produce in large quantities. They can be modified to meet different needs, but they may not interact as well with cells or have as much biological activity as natural polymers.

Since protein-based materials are biodegradable, biocompatible, and can be formed into supportive 3D structures that promote tissue growth, they are also commonly used as scaffold materials.

b. Ceramics and Glasses - Table 1 shows that ceramics used in scaffold development can be classified into bioinert and bioactive types depending on how they react with the tissue at the implant site. Ceramics and bioactive glasses are widely used in bone tissue engineering

due to their good osteoconductivity, high compressive strength, and compatibility with bone. Examples include hydroxyapatite (HA), tricalcium phosphate (TCP), and bioactive glass. However, these materials have some drawbacks, such as low toughness, difficulty in shaping, slow breakdown, and brittleness. To overcome these issues, ceramics are often combined with polymers or other materials to form composite scaffolds, which offer improved mechanical strength, biodegradability, and overall performance.

Table 1.Summary of ceramic materials used for making scaffolds. (Du et al., 2018).

Class	**Materials**	**Precursors**	**Properties**
Bioactive ceramic scaffold	Hydroxyapatite	Poly (acrylic acid), poly (lactic acid), photo-curable resin, poly caprolactone	Superior biocompatibility; can be used for cell adhesion, proliferation and differentiation
	Tricalcium phosphate	Hydroxypropyl methylcellulose, polymethacrylate, polyethyleneimine	Low compressive strength; biocompatibility and degradation ability in physiological environment
	Calcium silicate	Silicone polymer	Biaxial flexural strength; good cell viability, no cytotoxicity effect on the cells
	Mesoporous bioactive glasses	Polycaprolactone, poly (lactic acid), methylcellulose	Good bioactivity in vitro and in vivo for bone tissue regeneration
	bioactive glass		
	6P53B glass		
	Alkali-free bioactive Glass		

Class	Materials	Precursors	Properties
Bioinert ceramic scaffold	Alumina, alumina/borosilicate glass, alumina/SiC	Dextrin, urea, formaldehyde	Improved mechanical properties (tensile strength, flexural strength, compressive strength); lack of bioactivity
	Zirconia	Poly (vinyl alcohol), polycaprolactone	Interconnected architectures; lack of chemical bonding between tissues

c. Metals and Alloys

Bone tissue engineering often uses metals and alloys because of their good mechanical strength and ability to support weight-bearing applications. Commonly used materials include iron (Fe), magnesium (Mg), and titanium alloys. Iron has high strength, but some studies have noted issues such as inflammation and toxicity, which limit its use in the body. Magnesium and its alloys show promise due to their biodegradability, biocompatibility, and ability to stimulate bone cell growth, making them suitable for temporary implants. Titanium alloys are widely used due to their excellent strength, corrosion resistance, and porous structure that supports bone growth and integration. They are frequently used in implants and prosthetic devices.

d. Composites

Composites have gained interest among researchers because they allow the development of new materials with desirable properties from two or more components. The idea of combining different materials is to overcome the limitations of using a single material. Natural bone is a biological composite, so inorganic-organic composites (or hybrid scaffolds) have been widely studied for use in bone tissue regeneration. These composites include metal/metal, metal/polymer, ceramic/ceramic, ceramic/polymer, ceramic/hydrogel, and functional ceramic-based scaffolds. Among these, ceramic/polymer composites have recently gained recognition as bone tissue mimics. They offer the advantage of adjusting the ratio of organic and inorganic materials, which in turn changes the properties of the composite scaffold to better suit the needs of bone tissue engineering.

2.1.5 Various scaffold fabrication methods

Numerous fabrication technologies have been developed and reported for the designing of scaffolds and these techniques can be distinguished into two main types: conventional techniques and additive manufacturing techniques listed in Fig. 4. All methods used result in unique internal architecture of the scaffold with respect to pore size, structure,

interconnection and mechanical properties. In this section, different scaffolds manufacturing methods will be discussed.



Fig. 4. Various methods of creating an ideal scaffold for biomedical applications.

Table 2. Classification of conventional methods used for scaffold fabrication.

Manufacturing methods	**Source of energy**	**components**	**Advantages**	**Disadvantages**	**References**
Solvent casting and particulate leaching	Thermal energy	Polymer, Polymer composites	Economical	Solvent used is toxic	(Bajaj et al., 2014) (Li et al., 2016) (Subia et al., 2010)
			High porosity (50–90%)	Time-consuming process	(Kumar and Jacob, 2022)
			Pore sizes are adjustable		

Manufacturing methods	Source of energy	components	Advantages	Disadvantages	References
Freeze drying	Freezing	Polymer	Thermal protection	Energy intensive	(Toth et al., 1995) (Thavornyutikarn et al., 2014) (Kumar & Jacob, 2022)
			Highly porous and interconnectivity	Use of cytotoxic solvents	
			Controlling porosity	Labour intensive process	
Thermal Induced Phase Separation	Thermal energy	Thermoplastic polymer	Porous fibres greater than 95%	Limited materials	(Toth et al., 1995) (Kumar & Jacob, 2022) (Kim et al., 2014)
			Low defect probability	Poor resolution	
Gas Foaming	Thermal energy, Gas pressure	Polymer	Sponge structure with high porosity	Optimized heat usage	(Toth et al., 1995) (Kumar & Jacob, 2022) (Harris et at.,1998)
			Non-reactive gas used	Nonporous skin layer of closed and non-interconnected pore.	
			Cost-effective		

Manufacturing methods	Source of energy	components	Advantages	Disadvantages	References
Powder Foaming process	Thermal energy	Ceramics, Bioglass	Construction of porous ceramic scaffolds	Low protein binding	(Kumar & Jacob, 2022) (Chen, 2011) (Chen et al., 2006)
Sol-Gel	Thermal energy	Metals, Metal alkoxides, Ceramics, Glass	Ceramic engineering or manufactured glass materials	Mechanical resistance	(Kumar & Jacob, 2022) (Raucci et al., 2010) (Chen et al., 2010)
Electrospinning	High voltage electric field	Polymers	Production of nanofibrous scaffolds Develops polymers of high tensile strength	Organic solvents used are toxic Requires high voltage Poorly controlled porosity	(Kumar & Jacob, 2022) (Roseti et al., 2017) (Pham et al., 2006)

Table 3. various additive manufacturing techniques used for scaffold fabrication.

Method	Energy Source	Material used	Accuracy	Advantage	Disadvantage	Ref.
Stereo-lithography	UV laser	Photo-sensitive polymers	10–30 µm	High potential in the creation of different cell-based machines.	Resins used may be cytotoxic	(Du et al., 2018) (Bajaj et al., 2014) (Heller et al., 2009)
Fused Deposition Modelling	Thermal energy	Polymers, ceramic composite materials	200–500 µm	Highly porous structure without the use of solvents Scaffold with excellent mechanical strength was achieved	Requires size consistency in pre-formed fibres	(Du et al., 2018) (Chou et al., 2016) (Shor et al., 2009)
Selective Laser Sintering	Laser	Metal, ceramics (fine powder form)	700–1000 µm	No external support needed Capable of handling multiple materials in one platform	Slow process Bulky and rough surface. Post-processing required. Expensive	(Du et al., 2018)
Binder jetting technique	Thermal energy	Polymers, metal, ceramics	100–150 µm	Works with a wide range of materials	Channels require removal of	(Roseti et al., 2017) (Du et al., 2018)

Method	Energy Source	Material used	Accuracy	Advantage	Disadvantage	Ref.
					any unbound powders.	(Sachs et al., 1990)
				Does not require heat	Prone to clogging	
Ink Jet printing	Thermal energy	Droplets	100–150 µm	Low cost	Clogging of printer heads	(Eltom et al., 2019) (Du et al., 2018) (Abdelaal & Darwish, 2013)
				Enhanced printing efficiency	Limited material availability	
Laser-Assisted Bioprinting	Laser	Cells, polymeric hydrogels	10–100 µm	Free of nozzle clogging	Lower cell viability	(Roseti et al., 2017) (Du et al., 2018) (Ozbolat & Yu, 2013).
Direct Cell Writing	Thermal energy	Cells, viscous materials (inorganics/organic composite paste, hydrogels)	200–600 µm	Broad selection of biomaterials	Low resolution	(Roseti et al., 2017) (Du et al., 2018) (Seol et al., 2014)

1) Conventional techniques

There are many types of structures called scaffolds that were traditionally used for delivering drugs and were also used in tissue engineering. Traditional methods are used to design scaffolds with particular sizes and shapes of pores, but they are limited when it comes to creating specific internal structures and connections.

a) Particulate Leaching and Solvent Casting

This method involves dissolving a polymer in a solvent, adding small salt particles, and then removing the salt, which leaves behind pores. It is a simple and easy method that can be used in bone and cartilage tissue engineering at a low cost. It helps create very porous structures with controlled sizes. However, it is mostly used for simple shapes, and sometimes toxic residues from solvents may remain.



Fig. 5. Diagram of Solvent Casting and Particulate Leaching Technique.

b) Freeze Drying

Freeze drying is also called lyophilisation. It is a process where a polymer solution is frozen, and then the solvent is removed by sublimation, which creates a porous scaffold. This method is useful because it avoids high temperatures, which means the biological materials aren't damaged. It can be applied in many tissue engineering applications, but it has some issues like irregular pore sizes, longer processing times, and higher energy use.

c) Thermal Induced Phase Separation (TIPS)

The process of TIPS is based on cooling a polymer solution so that it separates into different phases, and when the solvent is removed, a porous scaffold is formed. This can create highly porous scaffolds and can allow for the inclusion of bioactive molecules. However, it has some problems like low structural precision and is not widely used in certain applications, such as bone tissue engineering.

d) Gas Foaming (GF)

Gas foaming involves adding an inert gas like carbon dioxide or nitrogen into a polymer to create a porous, sponge-like structure. It is useful for making scaffolds with high porosity, and it can be used in bone and nerve tissue engineering. However, it can create closed pores and reduce the interconnected structure, which can affect the ability of cells to move through the scaffold.



Fig. 6. Schematic representation of gas foaming process.

e. Powder foaming process

This technique is mainly used for ceramic and glass scaffolds. Fillers are added to a ceramic slurry, removed during heating, and are responsible for the pores. It forms highly porous and interconnected pore structures, which are beneficial for bone regeneration. But mechanical strength may still be a problem.

f. Sol gel

Glass and ceramic-based scaffolds are typically created by the sol-gel process. It enables the formation of various shapes and very porous structures. Such scaffolds can be used for bone repair, but they tend to have limited mechanical properties and could need additional modifications.

g. Electrospinning

The scaffolds have been created by an electrospinning technique using a high-voltage electric field that produces very fine fibers and closely mimics the natural ECM. Very versatile and can be used in skin and nerve healing as well as in wound healing. It also enables the incorporation of drugs and nanoparticles. Yet it tends to require organic solvents and is not very good at creating thick 3-D objects or those that are very complex.



Fig. 7. Schematic Illustration of an Electrospinning Setup for Scaffold Fabrication

Summary

Although traditional methods of making scaffolds have been important in tissue engineering, they have some issues when it comes to controlling the structure, mechanical strength, and scalability. These limitations have led to the development of more advanced techniques.

1. **Additive Manufacturing Techniques**

Scaffolds are made directly using additive manufacturing (also known as 3D printing or solid free-form fabrication) from computer-aided design models. One of the biggest advantages is the ability to create patient-specific and customized scaffolds, which is very

valuable in tissue and organ engineering. When combined with living cells, growth factors, and biomaterials, this process is called bioprinting.

a) Stereolithography (SLA)

SLA involves building a 3D object layer by layer by exposing a liquid resin to UV light. It offers very high precision and excellent resolution, which is useful for complex designs. However, some photosensitive resins can be toxic and affect biocompatibility.



Fig. 8. Schematic representation of stereolithography technique.

b) Fused Deposition Modeling (FDM)

FDM involves melting a thermoplastic polymer and extruding it layer by layer through a nozzle. It can create scaffolds with good mechanical properties, controlled porosity, and no toxic solvents. However, the high processing temperatures make it unsuitable for living cells and heat-sensitive materials.



Fig. 9. Schematic Representation of Fused Deposition Modeling Technique

c) Selective Laser Sintering (SLS)

SLS uses a powerful laser to fuse powder materials like polymers, ceramics, or metals into solid layers. It allows for easy control of the internal structure and is widely used in bone tissue engineering. However, it has high operating temperatures and requires removing excess powder after processing.



Fig. 10. Schematic representation of selective laser sintering technique.

d. Binder jetting technique

This is a technique in which the powder is layered on by a liquid binding agent to create a scaffold. It is low cost, quick and can be used to produce customized scaffolds. It is often, though, necessary to perform extra refining like sintering, and may present powder removal problems.

e. Inkjet Printing

Inkjet bioprinting applies small amounts of the bioink material to form 2D or 3D structures. It is also economical, rapid and maintains high cell viability and can be applied to tissue engineering. The primary problems it faces are nozzle blockages and printable materials.

f) Laser Assisted Bioprinting

LAB uses a laser to move bioink droplets onto a surface without using a nozzle. This avoids clogging and allows for high accuracy, excellent resolution, and strong cell viability. It is especially useful for printing complex tissues like bone, cartilage, and neural structures.

g) Direct Cell Writing

This is an extrusion-based bioprinting technique where cell-filled hydrogels are pushed through a nozzle to create 3D structures. It supports high-viscosity materials and high cell density, making it suitable for many tissue engineering applications. However, it has lower resolution and may still experience nozzle clogging.

3.Metal-Based Additive Manufacturing

In recent years, additive manufacturing has enabled the creation of metal-based scaffolds used in medical and dental applications. These methods allow precise control over porosity, strength, and implant design, making them ideal for patient-specific implants.

a. Selective Laser Melting (SLM)

SLM fully liquefies metal powders to generate robust, porous metal structures with a high-energy laser beam. It is commonly employed for bone implants, particularly in the case of titanium alloys. The most significant drawback is the surface roughness from partially melted particles.

b) Electron Beam Melting (EBM)

EBM is similar to SLM but uses an electron beam instead of a laser. It takes place in a vacuum and is widely used for making high-strength titanium implants that have good mechanical properties and bone compatibility.

c. Direct Energy Deposition (DED)

DED is a method that utilizes laser, electron beam or plasma to melt and deposit metal powders or wires layer by layer. It is primarily used to manufacture and repair metal implants and has excellent bone integration properties and high porosity.

d. Direct Material Laser Sintering (DMLS)

The DMLS process melts metal powders using a laser, building up the detailed metal structure, layer by layer. It is used extensively for orthopedic and dental implants, and has been used because it possesses good strength, controllable porosity and excellent customization that is suitable for patient-specific treatments.

2.2 NANOPARTICLE CLASSIFICATION AND PROPERTIES

2.2.1 CERAMIC NANOPARTICLES

Bioceramics, specially designed ceramic materials, used for repair and regeneration of damaged tissues. They are frequently employed for medical applications like bone fillers, porous scaffolds, implant coatings and bone cements. From their interaction with the body, Bioceramics fall broadly into three categories: bioinert, bioactive and bioresorbable ceramics.

i. Bioinert Ceramics

Bioinert ceramics like alumina and zirconia are known for their high mechanical strength and stability. They are commonly used for joint replacements and implants. But unlike the former, they do not directly link with the surrounding tissues and hence are not ideal candidates for scaffold construction in tissue engineering.

ii. Bioactive Ceramics

The hydroxyapatite, calcium phosphates, and bioactive glass are examples of bioactive ceramics that can bond directly with bone or soft tissue. The property enhances osteointegration and helps regeneration of tissues, they are very useful in designing scaffolds.

iii. Bioresorbable Ceramics

Bioresorbable ceramics are a type of material, like tricalcium phosphate (TCP), that will gradually disappear within the body and be replaced by newly formed tissues. They are

great for temporary scaffolds as they hold the structure up during healing and they are self-eroding once healing has been achieved.

The role and significance of properties in tissue engineering.

In tissue engineering, Bioceramics are crucial due to their properties of biocompatibility, osteoconductivity, and structural support. They are useful materials for developing advanced scaffolds because they promote the growth of tissues, integrate with the body, and in some cases, degrade safely.



Fig.11 Illustrates the different types of Bioceramics.

1. Bioinert Ceramics

Bioinert ceramics are materials that don't react with the body's tissues once they are placed inside the body. They are strong, resistant to wear and corrosion, and can hold up well under pressure, making them great for structural implants like hip and knee replacements. Some common types of these ceramics are alumina and zirconia.

- Alumina (Al_2O_3):

Alumina is chemically stable, meaning it doesn't react with other substances. It is very wear-resistant and works well with the body. Its smooth surface and low friction make it useful for dental implants, parts of the femur in prosthetics, bone screws, and joint replacements.

- Zirconia (ZrO_2):

Zirconia is tough and strong, thanks to how its structure changes under stress. It is also wear-resistant and works well with the body. It is used a lot in orthopedic and dental implants because of these qualities.

2. Bioactive Ceramics

Bioactive ceramics are materials that connect with living tissues and can form a direct bond with bones after being implanted. They help in the growth of new bone and the integration of the implant with the body. Some common types of these ceramics include calcium phosphate ceramics and bioactive glasses.

- Calcium Phosphate Ceramics:

Calcium phosphate ceramics are very compatible with the body and help in the growth of bone. They can form a layer of hydroxyapatite, which is similar to the mineral structure in bones. Hydroxyapatite (HA) and tricalcium phosphate (TCP) are used in bone grafts and tissue repair. However, they are not as strong as other materials, so they are not often used for parts that have to support a lot of weight.

- Bioactive Glasses:

Bioactive glasses, like Bioglass 45S5, can connect with both hard and soft tissues by forming a layer of hydroxycarbonate apatite. These materials are very active in the body, help in bone growth, and release ions that support the growth and development of cells.

3.Bioresorbable Ceramics

Bioresorbable ceramics break down over time inside the body and are replaced by natural bone tissue. These materials are considered advanced for use in tissue engineering and regenerative medicine.

- Mesoporous Bioactive Glass (MBG):

MBG has a large surface area and a controlled size of tiny spaces, which makes it very active in the body. It is widely studied for use in delivering drugs and helping in the regeneration of bone tissue because of its ability to form apatite quickly.

- Nanobioactive Glasses (NBGs):

Nanobioactive glasses have very small features and a large surface area, which helps them release ions more effectively. This leads to faster bone regrowth and better cell attachment. These glasses are more biologically active than regular bioactive glasses and are promising for making scaffolds and for regenerative medicine applications.

2.Metal/Metal oxide

Based on their composition, there are several broad categories for metal-based nanoparticles (NPs) including: metallic nanoparticles, metal oxide nanoparticles and magnetic nanoparticles. They are used in tissue engineering and regenerative medicine owing to their exclusive physicochemical properties like antibacterial activity, mechanical reinforcement, conductivity, catalytic behavior, and bioactivity.

1.Metallic Nanoparticles

Gold Nanoparticles (AuNPs)

The excellent biocompatibility, low toxicity and the ease of surface modification make gold nanoparticles popular. These are used in drug delivery, biosensing, cancer therapy and bone tissue engineering. AuNPs enhance bone regeneration via the Wnt/β-catenin, ERK/MAPK,

and p38/MAPK signaling pathways to promote osteogenic differentiation. They are also useful for delivering microRNAs which promote stem cell proliferation and repair of tissues.

Advantages: High biocompatibility, strong osteogenic potential, easy functionalization

Limitations**:** Dose-dependent cytotoxicity, possible ROS generation

- Silver Nanoparticles (AgNPs)

The antimicrobial activity is a major property of the silver nanoparticles. They are widely employed in wound dressings, coatings of implants, dental uses, and bone scaffolds. AgNPs may inhibit the growth of bacteria and promote osteogenesis, but excessive levels of AgNPs can cause cytotoxic effects.

Advantages: Excellent antibacterial activity, fights off wounds and bone growth

Limitations: Narrow therapeutic range, cytotoxic at high doses

- Copper Nanoparticles (CuNPs)

Copper plays a role in enzymatic reactions, collagen synthesis and angiogenesis, and is an essential trace element. The CuNPs promote cell proliferation, extracellular matrix formation, and vascularization, which are beneficial in tissue engineering.

Advantages**:** Promotes angiogenesis, strong antimicrobial activity, supports collagen formation

Limitations**:** Risk of inflammation and toxicity if uncontrolled

- Iron Nanoparticles (FeNPs)

Iron-based nanoparticles improve mechanical strength and scaffold performance. They also support cell attachment and proliferation, especially under magnetic stimulation.

Advantages: Mechanical reinforcement, magnetic responsiveness

Limitations: Metal ion release concerns, possible corrosion issues

- Zirconium Nanoparticles (ZrNPs)

Zirconium is very biocompatible, corrosion resistant and possesses high mechanical strength. It increases the hardness of the scaffolds and promotes cell growth and maturation.

- Aluminum Nanoparticles (Al_2O_3)

Aluminum oxide nanoparticles improve mechanical stability, fracture resistance, and scaffold durability. Their nanoscale surface properties influence cell adhesion and proliferation.

- Nickel Nanoparticles (NiNPs)

The shape memory, elasticity and strength of nickel-based materials make them useful in various applications, particularly in the area of fabricating porous scaffolds.

Limitation: May be toxic when used in very high doses.

2. Metal Oxide Nanoparticles

- Titanium Dioxide (TiO_2) Nanoparticles

TiO_2 nanoparticles improve mechanical strength, bioactivity, and osteointegration. TiO_2 nanotubes mimic the extracellular matrix (ECM), enhancing cell adhesion, proliferation, and differentiation. They also act as drug delivery reservoirs.

Applications: Bone implants, drug delivery, surface modification

- Cerium Oxide (CeO_2) Nanoparticles

Cerium oxide (nanoceria) possesses strong antioxidant properties due to reversible Ce^{3+}/Ce^{4+} redox cycling, enabling ROS scavenging.

Functions: Reduces oxidative stress, anti-inflammatory, promotes angiogenesis, enhances scaffold biocompatibility, antibacterial activity

Applications: Neural tissue engineering, wound healing, bone regeneration

3. Magnetic Nanoparticles

Common examples include: Magnetite (Fe_3O_4), Maghemite (γ-Fe_2O_3), Spinel ferrites

These exhibit superparamagnetic behavior, allowing control by external magnetic fields.

Applications: Targeted drug delivery, hyperthermia-based cancer treatment, stem cell tracking, improved scaffold performance, controlled release systems

Advantages: Remote controllability, enhanced tissue regeneration, multifunctionality

Conclusion

Metal-based nanoparticles provide multifunctional advantages in tissue engineering by enhancing mechanical properties, antibacterial activity, angiogenesis, osteogenesis, and targeted therapy. However, challenges such as toxicity, dosage optimization, and long-term biocompatibility must be addressed for safe clinical translation. This makes them promising materials for next-generation regenerative medicine and advanced biomaterial scaffolds.

3.carbon-based nanoparticle

Carbon-based nanoparticles have become a big deal in tissue engineering because of their special physical and chemical features. They have a large surface area, are strong and stable, conduct electricity, and are safe for the body. These qualities make them great for using in tissue engineering. They help cells stick better, grow faster, change into different types, and help tissues heal. These nanoparticles are usually divided into four groups:

1. Zero-dimensional (0D) nanomaterials

2.One-dimensional (1D) nanomaterials

3.Two-dimensional (2D) nanomaterials

4.Three-dimensional (3D) nanomaterials



Figure 12. Various carbon allotropes at the nanoscale, categorized into 0D, 1D, 2D, and 3D nanostructural forms

1. Zero-Dimensional (0D) Carbon-Based Nanomaterials

- Carbon Dots (C-Dots)

These are tiny carbon particles less than 10 nm in size.

They glow brightly, are stable, and are safe for the body.

Uses: Watching cells in the body, delivering medicine specifically, tracking tissue healing, combining treatment and imaging (Theranostics)

Advantage: They naturally glow, go to where they're needed, and are not harmful.

- Fullerene (C60)

Fullerenes have a unique ball-like shape and are good at fighting harmful molecules called reactive oxygen species (ROS). They help reduce damage from oxygen, keep skin cells healthy, and support tissue rebuilding.

Features: They protect cells from damage caused by oxygen.

Limitations: Need more work to make them safe for long-term use, and their safety is not fully known.

- Nanodiamonds (NDs)

They are strong, stable, and have a large surface area. They help create a structure similar to the natural environment around cells (extracellular matrix). They attract cells and guide them to become the right type, deliver medicine, and reduce cell damage from oxygen.

Advantages: They are safe, easy to modify, and can create 3D structures for scaffolds.

2.One-Dimensional (1D) Carbon-Based Nanomaterials

- Carbon Nanotubes (CNTs)

These are tube-like structures made of carbon, and they come in two types: single-walled and multi-walled. They make scaffolds stronger, help bones grow, and can carry growth factors and medicines.

Advantages: They are very strong, have bone-like strength, and help bones grow.

Uses: Repairing bones, making bone implants, delivering medicine using scaffolds.

Limitations: Safety depends on how they're cleaned and modified.

3.Two-Dimensional (2D) Carbon-Based Nanomaterials

- Graphene and Graphene Oxide (GO)

Graphene is a flat sheet of carbon, while GO has oxygen groups that help it mix with water and attach to proteins. They make scaffolds more flexible and stronger, help stem cells grow, and support bone growth.

Advantages: They are strong, have a large surface area, and are safe for the body.

Uses: Making scaffolds for bone tissue, supporting stem cells, creating composite materials.

- Reduced Graphene Oxide (rGO)

rGO helps scaffolds be stronger and helps cells interact better. It also helps cells grow and mimics the environment around cells.

Advantages: It conducts electricity better and makes scaffolds stronger.

Limitations: It can be harmful to some cells and needs modification on the surface.

4.Three-Dimensional (3D) Carbon-Based Nanomaterials

- Carbonized Polyacrylonitrile (cPAN) and Porous Carbon Scaffolds

To be used in scaffolds, traditional materials like graphite and diamond are made into porous forms.

Features: They have open spaces (75–100 micrometers), let cells and nutrients move through easily.

Benefits: They help cells survive better, encourage bone growth, and help calcium form.

In the body, they can repair bone damage effectively.

Advantages: They are strong, have good cell interaction, can carry drugs and growth factors, improve scaffold performance, and support bone and tissue healing.

Challenges: Some may be harmful if used in high amounts, there's not much long-term safety data, and they can clump together.

Conclusion

Using carbon-based nanoparticles in tissue engineering is a flexible and useful approach. These nanoparticles can make scaffolds stronger, have good biological effects, fight damage

from oxygen, and deliver drugs. They can copy the natural environment around cells and support cell functions, making them very promising for future medical treatments.

Table4 : Carbon nanomaterials and their applications.

Serial Number	Carbon Nanomaterial	Formulation	Tissue Engineering Applications
1	Carbon nanotubes	Hydrazide-functionalized carbon nanotubes–pericardial matrix derived hydrogel	Enhanced cardiac tissue engineering
2	Fullerene whisker scaffolds	Highly aligned 1D scaffold regulates cellular differentiation to muscle cells	Enhancement of myoblast maturation into myotube structures
3	Nanodiamond	Poly (lactic acid) and octadecyl amine-functionalized nanodiamond	Used as components of bone scaffolds and surgical tools in regenerative medicine
4	Carbon dots	CDs-based composite nanofibrous mats	Directed cell proliferation and enhancement of cellular functions
5	Carbon nanofibers	Electroactive CNF/gelatin (Gel) nanofibrous cardiac patches	Improved cell attachment and proliferation, accompanied by elevated gene expression and angiogenic activity
6	Graphene nanosheets	Biomimetic gelatin and bioactive glass scaffolds	High biocompatibility and optimized structural stiffness

4. Polymeric nanoparticle

Polymeric nanoparticles play an important role in tissue engineering because they are flexible in making scaffolds, delivering drugs, and supporting tissue repair. These polymers are usually categorized into three types: synthetic, natural, and composite systems.

Synthetic Polymers

Synthetic polymers like polyacrylamide, polyglycolic acid, and polyglycolide-co-caprolactone are commonly used in tissue engineering. They have adjustable mechanical features, predictable breakdown, and are easy to make into shapes. However, they are not naturally active, so they often need to be modified or have bioactive substances added to help cells interact better with the material.

1.Polylactic Acid (PLA)

PLA is made from natural sources like corn and sugarcane and can be broken down by the body. It is friendly to living tissues, has good mechanical properties, and breaks down over time. However, it is not very wet, which can stop cells from sticking to it. This might require changing its surface or adding something to make it more active.

2. Polyglycolic Acid (PGA)

PGA breaks down faster than PLA and is used for situations where the scaffold needs to dissolve quickly. However, it can break down too fast and weaken the structure, so it's better used with PLA to make PLGA, which has better performance.

3. Polycaprolactone (PCL)

PCL is a semi-crystalline polymer that takes a long time to break down, is strong and flexible, making it good for long-term and weight-bearing uses. It is not very wet and not naturally active, so it may need surface changes to improve its function.

4. Poly (lactic-co-glycolic acid) (PLGA)

PLGA has features of both PLA and PGA and can be adjusted in how fast it breaks down and how well it works with the body. It can release acidic byproducts that might affect the nearby tissues, so it is often combined with active materials to make it better

5.Poly (vinyl alcohol) (PVA)

PVA is a water-soluble, biocompatible material that is stable chemically and mechanically. It is not very active on its own and is often mixed with natural materials like gelatin or collagen to help cells stick better and increase biological activity.

Natural Polymers

Natural polymers are taken from living things and are widely used because they are naturally compatible with the body and can imitate the structure of the body's natural environment. This makes them good for cell interaction and tissue repair. However, they generally are not as strong as synthetic ones and break down in less predictable ways, which can be a problem for structures that need to support weight.

1.Collagen

Collagen is the most common protein in the body and is found in bones and connective tissues. It is not very likely to cause an immune reaction and has natural properties that encourage bone growth. It provides an environment that helps cells stick, move, grow, and

change. But it is not very strong and breaks down quickly, so it may need to be cross-linked or mixed with synthetic materials or ceramics to make it more stable.

2.Chitosan

Chitosan is made from chitin and is known for being biocompatible, biodegradable, and having antimicrobial properties. It helps cells stick and grow, and can be modified with growth factors or nanoparticles. However, it is not very strong and its breakdown is hard to predict, so it is often mixed with synthetic materials or ceramics.

3.Alginate

Alginate is taken from seaweed and is used because it is biocompatible, can break down, and can form gels. It is often used in scaffolds and gels with active molecules like hydroxyapatite or BMPs. However, it is not very strong and its breakdown is not easy to control, so it is often mixed with synthetic materials or nanoparticles to improve its strength.

Composite scaffolds

Composite scaffolds combine synthetic and natural polymers to balance mechanical strength with biological functions. They are designed to support structures that need to bear weight while also providing an environment that supports cell activity. Adding active materials or nanoparticles can improve their ability to help in tissue repair. A common example is mixing PCL with hydroxyapatite (HA), where PCL provides structure and HA improves activity and the ability to form minerals. Other blends, like PLGA with collagen or chitosan, mimic the natural environment while controlling breakdown and maintaining strength. These systems use the strengths of synthetic polymers and the active properties of natural ones, leading to better scaffolds. However, each material has its own trade-offs. For instance, PLA is strong but not flexible, while PCL is more flexible but not as active. Fabrication methods like freeze-drying make structures with lots of holes but don't control shape as well as 3D printing. These considerations show the need to design each scaffold to fit specific medical needs instead of using just one material or method.

2.3 Nanoparticle–Scaffold Integration Strategies

2.3.1 Overview

To enhance the functional behavior of tissue engineering constructs, nanoparticles need to be incorporated in scaffolds. The selected incorporation method affects the distribution, stability and release pattern of the nanoparticles and their interaction with cell. Poor integration can lead to aggregation, premature release or uneven distribution, which will diminish scaffold efficacy. Surface functionalization/coating, physical embedding in the bulk of the scaffold and chemical conjugation/crosslinking are the typical modes of integration of nanoparticles in the scaffold. Multifunctional scaffold design has recently attracted interest in hybrid designs using various strategies.

2.3.2 Surface Functionalization and Coating

Surface functionalization is a way to add things to the surface of a scaffold without changing the main structure, keeping the scaffold's strength but improving its activity on the surface.

- Physical Adsorption - This method uses weak forces like van der Waals and hydrogen bonds to attach nanoparticles. It is easy to use and remove, but the connection is not very strong.
- Layer-by-Layer (LbL) Assembly - This method alternates layers of charged particles to control how thick and how much of the nanoparticles are on the surface. It can be used to deliver different active agents in order and is often used to control how drugs or growth factors are released.
- Covalent Surface Grafting - This method uses chemical bonds to attach nanoparticles to the scaffold's surface. This improves the strength and stability of the connection and allows for precise placement of active molecules to improve cell interactions.

2.3.3 Physical Embedding Within the Scaffold Bulk

Physical embedding entails embedding the nanoparticles into the scaffold matrix during the scaffold production process, thereby impacting both biological and mechanical characteristics.

Blending and Casting- Preparation of polymer/hydrogel solutions containing nanoparticles prior to scaffold formation. This technique is typically applied for dispersion of hydroxyapatite, graphene, and iron oxide nanoparticles, and it is essential to prevent aggregation while performing this process.

Electrospinning- Incorporation of nanoparticles during electrospinning results in the production of controlled and sustained release of drug or growth factors to make ECM-like scaffolds.

3D Bioprinting- The use of bioinks containing nanoparticles allows for control over the spatial distribution of the nanoparticles and scaffolds with spatial variations in mechanical and biological properties can be fabricated.

2.3.4 Chemical Conjugation and Crosslinking

Chemical conjugation is a technique for creating stable covalent bonds between the nanoparticles and scaffold polymers, thereby assuring maximum retention and avoiding early release of the nanoparticles.

Crosslinker-Mediated Conjugation- Crosslinkers are used to link nanoparticles to the scaffolds, enhancing the strength, conductivity and degradation resistance of the scaffolds.

Click Chemistry- Efficient attachment of nanoparticles under mild conditions, whilst maintaining biological activity, has been achieved through highly selective biorthogonal reactions.

Ionic Crosslinking- In particular, in scaffolds containing cells, the electrostatic interactions are employed to create a network of hydrogels using nanoparticles as crosslinking points.

2.3.5 Stimuli-Responsive Integration Strategies

The “smart” systems allow nanoparticles to be controlled in their behaviour when triggered by external or biological stimuli.

- pH responsive: drugs are delivered in the acidic environment of wounds or tumours.
- Thermoresponsive systems: activate when temperatures change to release the product on demand.
- Magnetic and optical systems: induce drug release, mechanical stimulation or local heating using magnetic field or light.

2.3.6 Comparative Analysis and Selection Criteria

The type of integration is dependent on the type of nanoparticles, material of the scaffold, the tissue of interest, and the biological function of interest.

- Surface coating: Best for improving surface bioactivity, but maintains scaffold structure.
- Chemical embedding: desirable when nanoparticles are used to create composite materials with desirable changes in chemical characteristics.

2.4 Biological Interactions

2.4.1 Overview

A key part of making tissue engineering work is how nanoparticles, scaffolds, and the body's cells interact. These interactions influence how cells stick to surfaces, grow, change into different types, respond to the immune system, and help repair tissues. The best nanoparticle-scaffold systems should be safe for the body and also guide cells to act in ways that help build new tissues.

2.4.2 Cell–Nanoparticle Interactions

Nanoparticle Internalization and Intracellular Trafficking- Cells can take up nanoparticles from scaffolds via endocytosis. Uptake pathways and intracellular fate depend on their size, shape and surface chemistry. Drugs or genes can be delivered specifically via proper design and toxicity or oxidative stress is possible via poor design.

Cell Adhesion and Spreading- The surface nano-topography and chemistry of the scaffolds were altered to enhance cell attachment using nanoparticles. The functionalized nanoparticles with RGD peptides increase binding to integrin, formation of focal adhesion and spreading of cells.

Cell Proliferation- Nanoparticles, when present at optimal concentrations, can promote cell growth through release of bioactive molecules and/or enhancing the properties of scaffolds. Very high concentrations, however, may be used in a manner that inhibits proliferation because of their toxic effects.

Cell Differentiation- Biochemical and mechanical signals can guide the differentiation of stem cells by using nanoparticles. Hydroxyapatite has a pro-osteogenic effect, gold nanoparticles a pro-cardiac effect, and graphene-based materials a pro-neural effect, for instance.

2.4.3 Extracellular Matrix (ECM) Mimicry

Structural Mimicry- Nanoparticles can be used to mimic the nanoscale structure of native ECM, enhancing the stiffness, roughness, and topography of the scaffold, affecting cell behavior and tissue formation.

Biochemical Mimicry- Functionalized nanoparticles can be designed to provide an ECM-like signaling environment through delivery of growth factors or presentation of bioactive peptides, providing a more natural cell environment.

2.4.4 Immunomodulatory Effects

Innate Immune Response- Nanoparticles may induce immune responses including inflammation and activation of macrophages. Surface changes such as PEGylation also help to decrease immune recognition and compatibility.

Macrophage Polarization- To create anti-inflammatory “M2” macrophages that can facilitate repair rather than pro-inflammatory “M1” macrophages that can lead to fibrosis, scaffolds can be designed to encourage the polarization of these cells.

Adaptive Immune Response- Certain nanoparticles can trigger responses by the T cells or antibodies. Minimising these effects can be done by using biomimetic coatings and immunomodulatory agents.

2.4.5 Cell–Cell Communication-Nanoparticles can facilitate cell-to-cell communication via, increased electrical coupling, delivery of signaling molecules, and by mimicking natural exosomes. This aids in improved organization and regeneration of tissues.

CHAPTER 3

FUNCTIONAL ROLES OF NANOPARTICLES IN SCAFFOLDS

3.1 Mechanical Reinforcement

3.1.1 Overview

Conventional scaffold biomaterials frequently exhibit mechanical properties insufficient to withstand physiological loading conditions. Nanoparticle incorporation has emerged as an effective strategy for mechanical reinforcement, exploiting the exceptional intrinsic mechanical properties and high surface area-to-volume ratios of nanoscale materials to produce nanocomposite scaffolds with enhanced stiffness, strength, and toughness (Dvir et al., 2011; Rezwan et al., 2006).

3.1.2 Carbon-Based Nanoparticles

Carbon nanotubes (CNTs) exhibit tensile strengths of 13–52 GPa and elastic moduli of approximately 1 TPa, making them among the stiffest materials known (Treacy et al., 1996). At loading fractions as low as 0.1–1 wt%, CNTs produce substantial improvements in tensile strength and elastic modulus of polymer scaffolds through efficient load transfer facilitated by their high aspect ratio (Coleman et al., 2006). Graphene oxide incorporated into hydrogel scaffolds has demonstrated compressive moduli up to 3-fold higher than unreinforced controls at 1 wt% loading, with concurrent improvements in cell adhesion and osteogenic differentiation (Nair et al., 2013).

3.1.3 Ceramic Nanoparticles

Hydroxyapatite (HA) nanoparticles incorporated into PLGA, PCL, and collagen scaffolds increase compressive strength and elastic modulus in a concentration-dependent manner, with optimal mechanical reinforcement at 20–40 wt% loading — closely approximating native bone mineral content (Rezwan et al., 2006). Bioactive glass nanoparticles provide both mechanical reinforcement and osteoinductive bioactivity through silicon ion release that stimulates osteoblast proliferation and collagen synthesis (Hench, 2006).

3.1.4 Hydrogel Reinforcement

Nanosilicate clay particles incorporated into hydrogel scaffolds at only 1–5 wt% produce dramatic mechanical improvements through physical crosslinking between clay platelet surfaces and polymer chains, with elastic moduli up to 10-fold higher than unreinforced controls (Gaharwar et al., 2014). This reinforcement simultaneously enhances shear-thinning behavior beneficial for 3D bioprinting applications.

3.2 Controlled Drug and Growth Factor Delivery

3.2.1 Overview

Nanoparticles overcome the burst release limitations of conventional scaffold drug delivery by providing sustained, protective, and stimuli-responsive delivery of bioactive molecules

over therapeutically relevant timeframes, more faithfully replicating native ECM growth factor dynamics (Panyam & Labhasetwar, 2003).

3.2.2 Polymeric Nanoparticles

BMP-2-loaded PLGA nanoparticles incorporated into electrospun PCL scaffolds demonstrated sustained release over 8 weeks, achieving equivalent bone formation outcomes at 10–100 times lower doses than conventional delivery, significantly reducing risks of ectopic ossification (Ji et al., 2011). VEGF-loaded chitosan nanoparticles promoted sustained pro-angiogenic activity over 2–4 weeks, enhancing vascular ingrowth into scaffold constructs (Panyam & Labhasetwar, 2003).

3.2.3 Dual Growth Factor Delivery

Core-shell nanoparticle architectures enable sequential release of multiple growth factors from a single nanoparticle. Scaffolds delivering TGF-β followed by BMP-2 in a temporally offset manner produced more organized osteochondral constructs than simultaneous or single-factor delivery, demonstrating the importance of temporal signaling coordination (Dormer et al., 2012).

3.2.4 Stimuli-Responsive Release

Stimuli-responsive systems enable on-demand growth factor delivery through specific triggers:

pH-responsive-nanoparticles release antibiotics and growth factors in acidic wound environments (Schmaljohann, 2006)

Enzyme-responsive- systems release cargo in response to MMP activity during tissue remodeling (Lutolf & Hubbell, 2005)

Magnetic field-responsive- SPIONs release cargo through localized hyperthermia under alternating magnetic fields (Dobson, 2008)

Light-responsive- gold nanorods release cargo under near-infrared irradiation penetrating several centimeters of tissue (Huang et al., 2010)

3.2.5 Gene Delivery

Gene-activated scaffolds incorporating BMP-2 plasmid-loaded chitosan nanoparticles demonstrated sustained BMP-2 production by transfected MSCs over 2–4 weeks, driving robust osteogenic differentiation without viral vector safety concerns (Shea et al., 1999). siRNA-loaded nanoparticles targeting inhibitory genes including noggin and sclerostin complement growth factor delivery by removing molecular brakes on regeneration (Pannier & Shea, 2004).

3.3 Electrical and Magnetic Stimulation

3.3.1 Overview

Many tissues including cardiac muscle, skeletal muscle, and neural tissue are inherently electroactive. Conventional scaffold materials are electrically insulating and therefore incapable of supporting the bioelectrical signals essential for functional tissue maturation.

Conductive and magnetically responsive nanoparticles address this fundamental limitation (Dvir et al., 2011; Shin et al., 2013).

3.3.2 Conductive Nanoparticles

Gold nanowires- incorporated into alginate hydrogel cardiac scaffolds demonstrated synchronized cardiomyocyte contractile activity, gap junction protein expression, and electrical signal propagation velocities approaching native myocardium — outcomes entirely absent in non-conductive controls (Dvir et al., 2011).

Carbon nanotubes- incorporated into hydrogel scaffolds demonstrated enhanced cardiomyocyte maturation including organized sarcomeric structures, elevated cardiac troponin-T expression, and improved action potential conduction velocity (Shin et al., 2013). CNT scaffolds for neural tissue engineering similarly showed increased neurite outgrowth, greater synapse density, and directed neural stem cell differentiation toward neuronal lineages (Kam et al., 2009).

Graphene oxide- incorporated into electrospun scaffolds enhanced cardiomyocyte alignment, gap junction formation, and synchronized contractile activity while providing mechanical properties more closely approximating native myocardium than CNT-incorporated equivalents (Park et al., 2011).

3.3.3 Magnetic Nanoparticles

SPIONs incorporated into scaffold matrices enable remote mechanical stimulation through oscillating magnetic fields, promoting osteogenic differentiation of MSCs, chondrogenic matrix production, and cardiomyocyte maturation without surgical intervention (Dobson, 2008). Magnetic field-guided cell alignment using SPION-functionalized cells creates anisotropic constructs mimicking the organized cellular architecture of skeletal muscle, myocardium, and peripheral nerves (Huang et al., 2015).

3.4 Antibacterial Properties

3.4.1 Overview

Surgical site infection represents a major clinical challenge in tissue engineering, with antibiotic-resistant organisms increasingly prevalent. Nanoparticles with intrinsic antibacterial properties offer sustained local infection prevention without systemic toxicity or resistance selection pressure associated with conventional antibiotics (Hajipour et al., 2012).

3.4.2 Silver Nanoparticles

Silver nanoparticles exhibit broad-spectrum bactericidal activity through multiple concurrent mechanisms — membrane disruption, respiratory chain inhibition, ROS generation, and DNA damage — that minimize resistance development (AshaRani et al., 2009). AgNP-incorporated chitosan scaffolds demonstrated complete inhibition of MRSA and Pseudomonas aeruginosa growth at concentrations compatible with fibroblast and keratinocyte viability, with enhanced wound closure in diabetic rat models (Jayakumar et al., 2011). The primary challenge is the narrow therapeutic window between bactericidal and cytotoxic silver ion concentrations, addressable through PEG surface coating and polymer matrix-regulated release (Nel et al., 2006).

3.4.3 Zinc Oxide and Other Nanoparticles

Zinc oxide nanoparticles demonstrate comparable antibacterial efficacy to AgNPs with superior mammalian cell cytocompatibility, through membrane disruption, ROS generation, and zinc ion-mediated enzyme inhibition (Hajipour et al., 2012). Additional photocatalytic antibacterial activity under visible light provides an externally activatable infection prevention mechanism. Copper oxide nanoparticles uniquely combine antibacterial activity with pro-angiogenic function through HIF-1α activation, offering dual wound healing benefits (Gérard et al., 2010). Titanium dioxide nanoparticles provide photocatalytic antibacterial activity through hydroxyl radical generation that cannot be overcome through conventional resistance mechanisms (Webster et al., 2000).

3.4.4 Biofilm Prevention

Nanoparticles prevent initial bacterial attachment essential for biofilm formation through membrane disruption, ROS generation, and anti-adhesive surface modifications. Quorum sensing inhibitor-loaded nanoparticles disrupt bacterial cell-to-cell communication coordinating biofilm formation, providing a resistance-minimizing complement to bactericidal nanoparticle strategies (Hajipour et al., 2012).

3.5 Imaging and Diagnostics

3.5.1 Overview

Non-invasive monitoring of implanted scaffold fate, cell viability, tissue formation, and vascular ingrowth is essential for understanding regenerative mechanisms and guiding clinical management. Imaging-active nanoparticles enable real-time monitoring with molecular-level sensitivity beyond conventional clinical imaging capabilities (Shi et al., 2010; Bobo et al., 2016).

3.5.2 Iron Oxide Nanoparticles for MRI

SPIONs generate strong T_2 MRI contrast at nanomolar iron concentrations, enabling non-invasive cell tracking following implantation (Laurent et al., 2008). MSCs labelled with SPIONs have been tracked by MRI for up to 12 weeks in animal models, revealing previously uncharacterized patterns of cell migration within scaffold constructs. SPION-incorporated scaffold matrices additionally enable non-invasive monitoring of scaffold degradation in vivo, providing quantitative assessment of the coordination between scaffold breakdown and tissue formation (Bobo et al., 2016).

3.5.3 Gold Nanoparticles for CT and Photoacoustic Imaging

Gold nanoparticles provide strong X-ray attenuation approximately 2.7-fold greater than clinical iodine-based CT contrast agents, enabling high-resolution three-dimensional scaffold architectural visualization (Bhattacharya et al., 2010). Photoacoustic imaging using gold nanorods detects signals at tissue depths of several centimeters with sub-millimeter resolution, enabling non-invasive imaging of scaffold vascularization in anatomically relevant animal models (Huang et al., 2010).

3.5.4 Quantum Dots and Multimodal Imaging

Quantum dots offer 10–100-fold greater brightness and dramatically improved photostability compared to conventional fluorescent dyes, enabling long-duration real-time cell tracking (Shi et al., 2010). Multiplexed QD labeling simultaneously tracks multiple cell populations within complex constructs, revealing spatiotemporal dynamics of vascular network self-organization. Heavy metal-free alternatives including silicon and carbon dots are under development to address cadmium toxicity concerns (Nel et al., 2006). Multimodal nanoparticles combining MRI and optical or PET imaging capabilities provide complementary macroscopic and molecular-level spatial information essential for comprehensive preclinical scaffold evaluation (Bobo et al., 2016).

Chapter 4

Tissue-Specific Applications

4.1 Bone Tissue Engineering

4.1.1 Overview

Bone tissue engineering is a highly developed use of nanoparticle-based scaffolds because there's a big need for good ways to repair bones. Natural bone is made of a mix of hydroxyapatite (HA) and collagen, so many man-made scaffolds try to copy this structure by adding nanoparticles. This helps make the scaffolds stronger and better at supporting biological functions.

4.1.2 Hydroxyapatite (HA) Nanoparticles in Bone Scaffolds

HA nanoparticles are the most common materials used in bone engineering since they are similar to the mineral part of natural bone. They help make the scaffolds stronger, allow bone cells to stick to them, and encourage bone cell development by releasing calcium and phosphate ions. Scaffolds made with HA and other materials have been shown to help form new bone in both lab tests and in living animals.

4.1.3 Growth Factor-Loaded Nanoparticles for Osteogenesis

Growth factors like BMP-2 can be placed inside polymer nanoparticles and added to scaffolds so they can release the growth factors slowly. This method is better at helping new bone grow than just giving the growth factors all at once, and it also causes fewer side effects. Using both BMP-2 and VEGF together has been found to improve bone healing by helping both bone growth and the development of blood vessels.

4.1.4 Metallic and Carbon-Based Nanoparticles

Gold nanoparticles promote osteogenic differentiation and may improve electrical signaling between bone cells. Graphene oxide (GO) enhances scaffold stiffness and stimulates osteogenic pathways, leading to improved bone formation even at low concentrations.

4.1.5 3D-Printed Nanocomposite Bone Scaffolds

3D bioprinting enables fabrication of patient-specific bone scaffolds with precise architecture. Incorporating nanoparticles such as HA into bioinks improves mechanical properties and biological activity, while gradient designs can mimic natural bone structures more effectively.

4.2 Cartilage Tissue Engineering

4.2.1 Overview

Cartilage has limited self-repair capacity because it lacks blood vessels and nerves. Current treatments are often inadequate, making tissue engineering an important alternative. Nanoparticle-based scaffolds help mimic cartilage structure and provide biological signals for regeneration.

4.2.2 Chondrogenic Differentiation via Nanoparticle Cues

Nanoparticles loaded with growth factors such as TGF-β support long-term chondrogenic differentiation of mesenchymal stem cells (MSCs). Small molecules like kartogenin have also shown promise as stable alternatives for inducing cartilage formation.

4.2.3 Hydrogel–Nanoparticle Composites for Cartilage

Hydrogels are widely used in cartilage engineering because they resemble native cartilage ECM. Adding nanoparticles such as nanosilicates or cellulose nanocrystals improves mechanical strength and supports chondrocyte growth and matrix formation.

4.2.4 Osteochondral Interface Engineering

Repairing the cartilage–bone interface requires scaffolds with gradual changes in composition and mechanics. Gradient or bilayer nanoparticle-based scaffolds can simultaneously promote cartilage formation in one region and bone formation in another, improving osteochondral regeneration.

4.3 Neural Tissue Engineering

4.3.1 Overview

Neural tissue engineering addresses major clinical challenges such as spinal cord injury, peripheral nerve damage, traumatic brain injury, and neurodegenerative diseases (Bhattacharya et al., 2010). Regeneration in the central nervous system (CNS) is severely limited due to glial scar formation, inhibitory proteins, and lack of supportive growth substrates, while peripheral nervous system (PNS) regeneration is inadequate for nerve gaps greater than 3 cm (Kehoe et al., 2012). Nanoparticle-incorporated scaffolds aim to provide structural support, neurotrophic factor delivery, electrical conductivity, and nanoscale guidance cues to promote neuronal survival and regeneration (Bhattacharya et al., 2010; Kam et al., 2009).

4.3.2 Carbon Nanotube Scaffolds for Neural Tissue Engineering

Carbon nanotubes (CNTs) are extensively used in neural tissue engineering due to their electrical conductivity, nanoscale topography, and tunable mechanical properties (Kam et al., 2009). CNT-based hydrogel and electrospun scaffolds enhance neurite extension, synapse formation, and neuronal network connectivity compared with non-conductive scaffolds (Bhattacharya et al., 2010). Functionalization with laminin peptides or nerve growth factor (NGF) further improves neuronal adhesion and directed axonal growth. In vivo, NGF-functionalized CNT-collagen scaffolds have shown improved axonal regeneration and functional restoration of the rat sciatic nerve models (Kam et al., 2009).

4.3.3 Nerve Guidance Conduits with Nanoparticles

Nerve guidance conduits (NGCs) are clinically used for peripheral nerve repair, but current designs have limited regenerative capacity over long gaps (Kehoe et al., 2012). Incorporating nanoparticles improves their performance by enabling sustained neurotrophic factor delivery and enhanced structural guidance. NGF-loaded PLGA nanoparticles in electrospun PCL conduits provided sustained NGF release, improving axonal growth, myelination, and functional recovery in rat models (Panyam & Labhasetwar, 2003). Aligned

CNT-containing nanofibers further promote directional axonal growth through contact guidance.

4.3.4 Spinal Cord Injury Applications

Spinal cord injury (SCI) remains a major regenerative challenge due to glial scarring, inflammation, and inhibitory signaling (Bhattacharya et al., 2010). Injectable nanoparticle-loaded hydrogels are attractive because they conform to irregular lesion cavities with minimal surgical trauma. Multifunctional systems combining BDNF-loaded nanoparticles, anti-inflammatory agents, and chondroitinase ABC have shown potential to promote neuroprotection, axonal regeneration, and scar degradation. Nanoparticle-mediated siRNA delivery targeting scar-associated genes such as GFAP and vimentin offers an additional strategy to improve the regenerative microenvironment (Pannier & Shea, 2004).

4.4 Cardiac Tissue Engineering

4.4.1 Overview

cardiovascular disease is the leading global cause of death, with myocardial infarction (MI) causing irreversible loss of cardiomyocytes and resulting in heart failure (Mozaffarian et al., 2016). Because the adult heart has very limited regenerative capacity, damaged myocardium is replaced by scar tissue, reducing cardiac function (Bergmann et al., 2009). Cardiac tissue engineering aims to restore functional myocardium using cells, scaffolds, and growth factors. Nanoparticles are particularly valuable because they improve scaffold conductivity, mechanical compatibility, and support for the beating heart (Dvir et al., 2011).

4.4.2 Gold Nanoparticle-Enhanced Cardiac Constructs

Gold nanoparticles are widely used in cardiac scaffolds due to their excellent biocompatibility and electrical conductivity. They improve cardiomyocyte organization, gap junction formation, and synchronized contraction, enhancing overall cardiac patch performance (Dvir et al., 2011). Gold nanoparticle-based hydrogels also promote cell maturation and can enable non-invasive optical pacing through photothermal stimulation (Noor et al., 2019; Shi et al., 2010).

4.4.3 Carbon-Based Nanoparticles in Cardiac Scaffolds

Carbon nanotubes (CNTs) improve cardiomyocyte maturation, contractility, and electrical conduction in scaffold systems, leading to better cardiac repair in MI models (Shin et al., 2013). Graphene oxide (GO) also enhances cardiomyocyte alignment and synchronized beating while providing mechanical properties closer to native myocardium, reducing implant mismatch (Park et al., 2011; Bajaj et al., 2014).

4.4.4 Vascularization Strategies in Cardiac Scaffolds

Adequate vascularization is essential because cardiac tissue has high oxygen demands (Radisic et al., 2006). VEGF-loaded nanoparticles promote sustained angiogenesis and improve blood vessel formation within cardiac patches (Ferrara et al., 2003). Dual delivery of VEGF with IGF-1 or HGF further enhances cardiomyocyte survival and cardiac recovery. Injectable nanoparticle-hydrogel systems offer a minimally invasive alternative for delivering these therapies directly to infarcted myocardium (Formiga et al., 2014).

4.4.5 Personalized Cardiac Patches

Advances in 3D bioprinting have enabled patient-specific cardiac patches using autologous

cells and biomaterials. Noor et al. (2019) demonstrated bioprinted vascularized cardiac patches and miniature hearts, where gold nanoparticles improved electrical coupling and synchronized contraction. Although still experimental, this approach represents a promising future direction for personalized cardiac regeneration.

4.5 Skin and Wound Healing

4.5.1 Overview

Skin repair is a major tissue engineering challenge, especially in chronic wounds such as diabetic ulcers and pressure sores, which often heal poorly with conventional treatments (Sen et al., 2009). Nanoparticle-incorporated scaffolds offer advanced solutions by promoting wound closure, preventing infection, and supporting functional skin regeneration. These systems aim to mimic both the epidermal and dermal layers of native skin (Bhattacharya et al., 2010).

4.5.2 Antibacterial Nanoparticle Scaffolds for Wound Healing

Infection is a major barrier to wound healing. Silver nanoparticles (AgNPs) are widely used in chitosan and collagen scaffolds due to their strong antibacterial activity against pathogens like *S. aureus* and *P. aeruginosa*, while also promoting cell migration and wound closure (Jayakumar et al., 2011). Zinc oxide (ZnO) nanoparticles provide similar antibacterial effects with better cytocompatibility and additional photocatalytic activity, making them promising alternatives (Hajipour et al., 2012).

4.5.3 Growth Factor Delivery for Wound Healing

Nanoparticles enable sustained delivery of key growth factors such as EGF and PDGF, protecting them from degradation and improving wound healing outcomes. EGF-loaded nanoparticles enhance keratinocyte proliferation and re-epithelialization, while PDGF-loaded systems show superior healing compared to conventional treatments (Bhattacharya et al., 2010; Sen et al., 2009).

4.5.4 Angiogenesis Promotion in Wound Healing Scaffolds

Poor blood vessel formation is a major cause of chronic wound persistence. VEGF-loaded nanoparticles improve angiogenesis and accelerate healing, especially in diabetic wounds (Ferrara et al., 2003). Copper oxide nanoparticles provide dual benefits by promoting angiogenesis through HIF-1α activation while also offering antibacterial effects (Gérard et al., 2010).

4.5.5 Skin Appendage Regeneration

Regenerating skin appendages such as hair follicles and sweat glands remains a major challenge. Nanoparticle-mediated delivery of signaling molecules like Wnt activators and Sonic hedgehog (Shh) has shown potential to stimulate appendage formation, suggesting future possibilities for fully functional skin regeneration beyond simple wound closure (Bhattacharya et al., 2010).

Chapter 5

Biocompatibility, Toxicity, and Safety Considerations

5.1 Cytotoxicity Mechanisms of Nanoparticles

5.1.1 Overview

Nanoparticle cytotoxicity is a major safety concern in tissue engineering. Toxicity depends on size, shape, surface chemistry, dose, exposure time, and the biological environment. Understanding these mechanisms helps design safer nanoparticle-scaffold systems.

5.1.2 Physical Membrane Disruption

Nanoparticles can damage cell membranes through direct interaction with lipid bilayers. Cationic, hydrophobic, and high-aspect-ratio nanoparticles may cause membrane thinning, pore formation, or rupture, leading to impaired cell function or death.

5.1.3 Oxidative Stress Induction

Oxidative stress is the most common mechanism of nanoparticle toxicity. Nanoparticles generate reactive oxygen species (ROS), causing damage to DNA, proteins, and lipids. Mild ROS activates protective pathways, while excessive ROS triggers inflammation and apoptosis.

5.1.4 Mitochondrial Dysfunction

Nanoparticles can damage mitochondria by disrupting membrane potential and ATP production, increasing ROS generation, and activating apoptotic pathways, resulting in energy failure and cell death.

5.1.5 DNA Damage and Genotoxicity

Nanoparticles may cause DNA strand breaks, mutations, and chromosomal abnormalities through direct interaction or oxidative stress. Persistent damage can increase the risk of malignant transformation.

5.1.6 Lysosomal Dysfunction and Autophagy Impairment

Nanoparticles often accumulate in lysosomes, causing membrane damage, enzyme dysfunction, and impaired autophagy. This leads to waste accumulation, organelle damage, and eventual cell death.

5.2 Oxidative Stress and Inflammatory Responses

5.2.1 Nanoparticle-Induced Inflammation

Nanoparticles can activate immune pathways, triggering cytokine release and inflammation. This may occur through direct receptor activation, complement activation, or damage-associated signals.

5.2.2 NLRP3 Inflammasome and Toxicity

The NLRP3 inflammasome is a major mediator of nanoparticle-induced inflammation, promoting IL-1β release. Surface reactivity, high surface area, and fibrous shape increase activation risk.

5.2.3 Chronic Inflammation and Fibrosis

Long-term inflammation can lead to fibrotic capsule formation around implants, limiting tissue integration and causing scaffold failure. Surface engineering and macrophage modulation help reduce this response.

5.3 In Vitro vs. In Vivo Safety Assessment

5.3.1 In Vitro Cytotoxicity Testing

Standard tests evaluate viability, membrane damage, oxidative stress, apoptosis, and genotoxicity. However, nanoparticles may interfere with assay signals, requiring multiple testing methods.

5.3.2 Advanced In Vitro Models

3D cultures, organoids, organ-on-chip systems, and immune co-cultures better mimic physiological conditions and improve prediction of in vivo toxicity.

5.3.3 In Vivo Safety Assessment

Animal studies assess biodistribution, organ toxicity, immune response, and long-term effects. ISO 10993 guidelines are commonly used for preclinical evaluation.

5.3.4 Linking In Vitro and In Vivo Studies
Physiologically based pharmacokinetic (PBPK) models are utilized to estimate in vivo toxicity using in vitro experimental data, thereby enhancing safety evaluation while minimizing dependence on animal-based testing.

5.4 Regulatory Frameworks

5.4.1 FDA Framework

The FDA evaluates nanoparticle-based scaffolds based on size-dependent properties, requiring detailed physicochemical characterization and ISO 10993 biocompatibility testing.

5.4.2 EMA Framework

The EMA requires detailed nanoparticle characterization and strict evaluation under European medical device regulations, especially for implantable devices.

5.4.3 ISO Standards

ISO 10993 provides international standards for cytotoxicity, implantation effects, leachable, and nanomaterial-specific safety assessment.

5.4.4 Emerging Approaches

New OECD and regulatory guidelines are being developed to address unique safety challenges of nanoparticle-based tissue engineering products.

5.5 Strategies to Mitigate Nanotoxicity

5.5.1 Surface Modification

PEGylation, zwitterionic coatings, and biomimetic membranes reduce protein adsorption, immune recognition, and cytotoxicity.

5.5.2 Size and Shape Optimization

Smaller, spherical nanoparticles generally show lower toxicity and better clearance than larger or fibrous particles like long CNTs.

5.5.3 Biodegradable Nanoparticle Design

Using biodegradable materials such as PLGA, PLA, and chitosan minimizes long-term accumulation and chronic toxicity.

5.5.4 Antioxidant Strategies

Antioxidant nanoparticles like cerium oxide and antioxidant-loaded carriers reduce ROS-related toxicity and support tissue healing.

5.5.5 Dose Optimization

Determining the therapeutic window and NOAEL ensures nanoparticles provide benefits without harmful side effects.

Chapter 6

Challenges and future direction

6.1 Scalability and Manufacturing Limitations

6.1.1 Overview

The transition of nanoparticle-incorporated scaffolds from laboratory prototypes to clinically manufacturable products remain one of the most formidable translational challenges in tissue engineering. Most constructs are fabricated at small scales using labour-intensive bench-top processes incompatible with clinical-grade manufacturing requirements (Mao & Mooney, 2015; Huebsch & Mooney, 2009).

6.1.2 Nanoparticle Synthesis Scalability

Batch-to-batch variability in nanoparticle size, surface chemistry, and drug loading efficiency arises from fluctuations in reagent quality, temperature gradients, and mixing dynamics at larger scales (Farokhzad & Langer, 2009). Even minor size variations of 10–20 nm can significantly alter cellular uptake, drug release kinetics, and immunological recognition (Nel et al., 2009). Microfluidic synthesis platforms offer improved reproducibility through precise continuous-flow processing and can be parallelized to achieve clinical production throughputs (Valencia et al., 2012).

6.1.3 Scaffold Fabrication Scale-Up

Electrospinning produces nanofibers at only 0.01–0.1 g/hour — wholly inadequate for clinical-scale fabrication (Bhardwaj & Kundu, 2010). Multineedle and needleless systems increase throughput but introduce challenges in maintaining uniform fiber diameter and nanoparticle distribution. Current 3D bioprinting systems require hours to days to fabricate clinically relevant constructs, and nanoparticle incorporation alters bioink rheology causing nozzle clogging and inconsistent extrusion (Murphy & Atala, 2014). Volumetric bioprinting fabricating entire constructs simultaneously through tomographic light projection represents a transformative speed advance, producing centimetre-scale constructs in under 30 seconds (Kelly et al., 2019).

6.1.4 Sterilization and Quality Control

Conventional sterilization methods present significant challenges. Autoclaving degrades thermolabile scaffolds; gamma irradiation reduces polyester molecular weight by up to 50%; ethylene oxide reacts with nanoparticle surface groups (Holy et al., 2000). Supercritical carbon dioxide sterilization represents a promising alternative, preserving scaffold architecture and growth factor bioactivity (Qiu et al., 2009). GMP compliance imposes stringent documentation, process validation, and environmental monitoring requirements that represent substantial burdens for early-stage developers (Williams, 2019).

6.2 Long-Term Biodegradation and Clearance

6.2.1 Overview

The long-term fate of nanoparticle-incorporated scaffold components in vivo remains incompletely understood, representing a significant safety and regulatory concern. The ideal

construct should degrade commensurately with tissue formation without generating toxic degradation products or persistent nanoparticulate residues (Nair & Laurencin, 2007).

6.2.2 Scaffold Matrix Degradation

Natural polymer scaffolds degrade through enzymatic hydrolysis at rates dependent on local enzyme concentrations — inherently variable and difficult to control precisely (Lee & Mooney, 2001). Synthetic polyester scaffolds generate acidic degradation products that create autocatalytic pH drops in scaffold interiors, compromising cell viability (Grayson et al., 2008). Basic ceramic nanoparticles including hydroxyapatite buffer these acidic products, attenuating autocatalytic degradation — a significant advantage beyond their structural and biological roles (Rezwan et al., 2006)

6.3 Vascularization of Thick Scaffolds

6.3.1 Overview

Vascularization remains the most profound unsolved challenge in scaffold tissue engineering. All cells must reside within 100–200 μm of a capillary for adequate oxygen supply, yet host vascular ingrowth proceeds at only 1–5 μm per hour — far too slow to rescue cells in thick construct interiors (Rouwkema et al., 2008; Folkman & Hochberg, 1973).

6.3.2 Nanoparticle-Based Vascularization Strategies

Growth factor delivery: VEGF-loaded PLGA nanoparticles incorporated into scaffold matrices demonstrated significantly enhanced vascular ingrowth compared to surface-adsorbed VEGF, attributed to extended-release duration and protection from proteolytic degradation (Panyam & Labhasetwar, 2003). Dual delivery of VEGF and PDGF-BB in temporally offset fashion produced more mature and structurally stable vessels than single-factor delivery (Richardson et al., 2001).

Oxygen-generating nanoparticles: Calcium peroxide nanoparticles generate oxygen through sustained reaction with water, directly supplementing oxygen supply during the prevascularization period (Ward et al., 2013). Perfluorocarbon nanoparticles — with oxygen-dissolving capacity 50 times higher than water — provide passive demand-driven oxygen release in response to local hypoxia (Riess, 2001).

Pre-vascularization: Co-incorporation of endothelial progenitor cells with angiogenic factor-loaded nanoparticles promotes vasculogenesis within scaffold constructs prior to implantation, accelerating vascular anastomosis with host vessels following surgery (Rouwkema et al., 2008).

6.3.3 Remaining Challenges

Vascular networks formed through current strategies lack the hierarchical organization — from arteries through arterioles, capillaries, and venules — necessary for efficient perfusion throughout thick constructs (Novosel et al., 2011). Surgical anastomosis of scaffold microvascular networks with host capillaries remains technically demanding and represents a critical unmet engineering challenge whose resolution would transform the clinical feasibility of thick tissue constructs (Rouwkema et al., 2008).

6.4 Emerging Trends

6.4.1 4D Bioprinting with Nanoparticles

4D bioprinting extends 3D bioprinting by incorporating time as a fourth dimension — producing constructs that change shape, stiffness, or biological activity in response to environmental stimuli following fabrication (Gao et al., 2016). Nanoparticles are central to 4D bioprinting functionality, with thermoresponsive, magnetically responsive, and pH-sensitive nanoparticles enabling programmed structural transformations and on-demand bioactive signal release that adapt construct properties to the evolving tissue regeneration environment (Stuart et al., 2010).

6.4.2 AI-Driven Scaffold Design

AI and ML are transforming nanoparticle–scaffold design by enabling computational prediction of relationships between nanoparticle physicochemical properties, scaffold parameters, and biological outcomes with speed exceeding empirical experimentation (Langer & Tirrell, 2004). Machine learning models trained on large experimental datasets can identify non-intuitive design parameter relationships, optimize multi-variable scaffold formulations simultaneously, and predict nanotoxicity profiles dramatically accelerating the design-test-optimize cycle that currently limits regenerative medicine innovation (Williams, 2019).

6.4.3 Personalized Nano-Scaffold Platforms

Patient-specific nanoparticle-incorporated scaffold constructs-fabricated from autologous iPSC-derived cells using patient-specific bioink formulations and personalized geometry derived from medical imaging - represent the ultimate aspiration of tissue engineering personalization (Noor et al., 2019). The landmark demonstration of 3D-bioprinted personalized cardiac patches incorporating gold nanoparticles from patient-derived omentum established proof-of-concept for this vision, though significant scale-up, safety validation, and manufacturing challenges remain before clinical realization (Noor et al., 2019).

6.4.4 Exosome–Nanoparticle Hybrid Systems

Exosome-mimetic nanoparticles engineered to replicate the surface biochemistry and cargo-transfer functions of naturally secreted exosomes represent an emerging bridge between synthetic nanotechnology and natural cell–cell communication (Hu et al., 2011). These hybrid systems deliver bioactive microRNAs, proteins, and lipids to cells within scaffold microenvironments through mechanisms indistinguishable from natural paracrine signaling, promoting angiogenesis, attenuating apoptosis, and modulating immune responses with exceptional biological specificity (Lener et al., 2015). Their integration into scaffold constructs represents a frontier of nanoparticle tissue engineering that blurs the boundary between engineered nanomedicine and natural biology.

Chapter 7

CONCLUSION

Nanoparticle incorporation into scaffold tissue engineering represents a transformative advance in regenerative medicine, addressing the fundamental limitations of conventional scaffold systems through a level of functional sophistication that closely approaches the complexity of native tissue microenvironments. This thesis has demonstrated that nanoparticles contribute to scaffold performance through five principal mechanisms — mechanical reinforcement, controlled bioactive molecule delivery, electrical and magnetic stimulation, antibacterial protection, and bioimaging — each addressing specific deficiencies of conventional biomaterials that have historically constrained the clinical impact of tissue engineering (Dvir et al., 2011; Khademhosseini & Langer, 2016). The tissue-specific application analysis revealed significant advances across bone, cartilage, neural, cardiac, and skin tissue engineering, with hydroxyapatite nanoparticle-incorporated scaffolds approaching clinical translation for bone regeneration, conductive gold and carbon nanotube scaffolds transforming cardiac and neural tissue engineering, and multifunctional antibacterial nanoparticle scaffolds demonstrating compelling efficacy for chronic wound healing (Rezwan et al., 2006; Dvir et al., 2011; Jayakumar et al., 2011). Across all applications, the biomimicry principle designing nanoparticle–scaffold systems that most faithfully replicate the nanoscale architecture and biochemical dynamics of native ECM emerged as the most reliable predictor of superior biological outcomes (Stevens & George, 2005). The nanotoxicological analysis established that nanoparticle cytotoxicity is not an immutable property but can be substantially mitigated through rational surface modification, size optimization, biodegradable material selection, and careful dose management within validated therapeutic windows (Nel et al., 2009). The regulatory frameworks established by the FDA, EMA, and ISO provide structured pathways for clinical translation that, while still evolving, offer clear guidance for developers committed to rigorous safety evaluation. Significant challenges remain. Scalability of nanoparticle synthesis and scaffold fabrication, long-term biodegradation and clearance of non-biodegradable nanoparticles, vascularization of thick constructs, and the organizational and economic barriers to clinical translation collectively represent formidable obstacles whose resolution requires sustained multidisciplinary effort integrating materials science, cell biology, manufacturing engineering, regulatory science, and health economics (Mao & Mooney, 2015; Williams, 2019). Emerging strategies including 4D bioprinting, AI-assisted scaffold design, personalized iPSC-based constructs, and exosome–nanoparticle hybrid systems offer promising trajectories for overcoming these barriers in the coming decade.

Ultimately, the millions of patients worldwide suffering from conditions requiring tissue repair or replacement for whom existing treatments provide only partial and temporary relief provide the fundamental motivation for advancing this field with both scientific rigor and translational urgency. The evidence synthesized in this thesis supports a measured but genuine optimism that nanoparticle-enhanced scaffold tissue engineering will progressively fulfil its transformative clinical potential, moving from laboratory innovation to tangible therapeutic benefit for patients in need.

REFRENCES

1. Abdelaal, O. A., & Darwish, S. M. (2013). Review of rapid prototyping techniques for tissue engineering scaffolds fabrication. In Characterization and Development of Biosystems and Biomaterials (pp. 33–54). Springer.
2. Arcos, D., & Vallet-Regí, M. (2020). Substituted hydroxyapatite coatings of bone implants. Journal of Materials Chemistry B, 8, 1781–1800. https://doi.org/10.1039/C9TB02710F
3. AshaRani, P. V., Low Kah Mun, G., Hande, M. P., & Valiyaveettil, S. (2009). Cytotoxicity and genotoxicity of silver nanoparticles in human cells. ACS Nano, 3(2), 279–290.
4. Bajaj, P., Schweller, R. M., Khademhosseini, A., West, J. L., & Bashir, R. (2014). 3D biofabrication strategies for tissue engineering and regenerative medicine. Annual Review of Biomedical Engineering, 16, 247–276.
5. Balasubramanian, S. K., Jittiwat, J., Manikandan, J., Ong, C. N., Yu, L. E., & Ong, W. Y. (2010). Biodistribution of gold nanoparticles and gene expression changes in the liver and spleen after intravenous administration in rats. Biomaterials, 31(8), 2034–2042.
6. Beig, B., Liaqat, U., Niazi, M. F. K., Douna, I., Zahoor, M., & Niazi, M. B. K. (2020). Current challenges and innovative developments in hydroxyapatite-based coatings on metallic materials for bone implantation: A review. Coatings, 10, 1249. https://doi.org/10.3390/coatings10121249
7. Bhardwaj, N., & Kundu, S. C. (2010). Electrospinning: A fascinating fiber fabrication technique. Biotechnology Advances, 28(3), 325–347.
8. Bhattacharya, R., Mukherjee, P., & Bhattacharya, A. (2010). Biological properties of naked metal nanoparticles. Advanced Drug Delivery Reviews, 60(11), 1289–1306.
9. Bobo, D., Robinson, K. J., Islam, J., Thurecht, K. J., & Corrie, S. R. (2016). Nanoparticle-based medicines: A review of FDA-approved materials and clinical trials to date. *Pharmaceutical Research*, 33(10), 2373–2387.
10. Buss, D. J., Kröger, R., McKee, M. D., & Reznikov, N. (2021). Hierarchical organization of bone in three dimensions: A twist of twists. Journal of Structural Biology X, 6, 100057. https://doi.org/10.1016/j.yjsbx.2021.100057
11. Chen, Q. Z. (2011). Foaming technology of tissue engineering scaffolds: A review. Bubble Science, Engineering and Technology, 3(2), 34–47.
12. Chen, Q. Z., Li, Y., Jin, L. Y., Quinn, J. M., & Komesaroff, P. A. (2010). A new sol–gel process for producing Na_2O-containing bioactive glass ceramics. Acta Biomaterialia, 6(10), 4143–4153.
13. Chen, Q. Z., Thompson, I. D., & Boccaccini, A. R. (2006). 45S5 Bioglass®-derived glass–ceramic scaffolds for bone tissue engineering. Biomaterials, 27(11), 2414–2425.
14. Chen, R. R., & Mooney, D. J. (2003). Polymeric growth factor delivery strategies for tissue engineering. *Pharmaceutical Research*, 20(8), 1103–1112.
15. Chou, Y. C., Lee, D., Chang, T. M., Hsu, Y. H., Yu, Y. H., Liu, S. J., & Ueng, S. W. (2016). Development of a three-dimensional (3D) printed biodegradable cage to convert morselized corticocancellous bone chips into a structured cortical bone graft. International Journal of Molecular Sciences, 17(4), 595.
16. Coleman, J. N., Khan, U., Blau, W. J., & Gun'ko, Y. K. (2006). Small but strong: A review of the mechanical properties of carbon nanotube–polymer composites. Carbon, 44(9), 1624–1652.
17. Dalby, M. J., Gadegaard, N., Tare, R., Andar, A., Riehle, M. O., Herzyk, P., ... & Oreffo, R. O. C. (2007). The control of human mesenchymal cell differentiation using nanoscale symmetry and disorder. *Nature Materials*, 6(12), 997–1003.
18. Dobrovolskaia, M. A., & McNeil, S. E. (2007). Immunological properties of engineered nanomaterials. Nature Nanotechnology, 2(8), 469–478.

19. Dobson, J. (2008). Remote control of cellular behaviour with magnetic nanoparticles. Nature Nanotechnology, 3(3), 139–143.
20. Dormer, N. H., Berkland, C. J., & Detamore, M. S. (2012). Emerging techniques in stratified designs and continuous gradients for tissue engineering of interfaces. Annals of Biomedical Engineering, 38(6), 2121–2141.
21. Du, X., Fu, S., & Zhu, Y. (2018). 3D printing of ceramic-based scaffolds for bone tissue engineering: An overview. Journal of Materials Chemistry B, 6(27), 4397–4412.
22. Dvir, T., Timko, B. P., Kohane, D. S., & Langer, R. (2011). Nanotechnological strategies for engineering complex tissues. *Nature Nanotechnology*, 6(1), 13–22.
23. Eltom, A., Zhong, G., & Muhammad, A. (2019). Scaffold techniques and designs in tissue engineering functions and purposes: A review. Advances in Materials Science and Engineering, 2019, 1–13.
24. Engler, A. J., Sen, S., Sweeney, H. L., & Discher, D. E. (2006). Matrix elasticity directs stem cell lineage specification. *Cell*, 126(4), 677–689.
25. Farokhzad, O. C., & Langer, R. (2009). Impact of nanotechnology on drug delivery. ACS Nano, 3(1), 16–20.
26. Ferrara, N., Gerber, H. P., & LeCouter, J. (2003). The biology of VEGF and its receptors. *Nature Medicine*, 9(6), 669–676.
27. Feynman, R. P. (1960). There's plenty of room at the bottom. *Engineering and Science*, 23(5), 22–36.
28. Folkman, J., & Hochberg, M. (1973). Self-regulation of growth in three dimensions. Journal of Experimental Medicine, 138(4), 745–753.
29. Fu, L., Engqvist, H., & Xia, W. (2020). Glass-ceramics in dentistry: A review. Materials, 13, 1049. https://doi.org/10.3390/ma13051049
30. Gaharwar, A. K., Peppas, N. A., & Khademhosseini, A. (2014). Nanocomposite hydrogels for biomedical applications. Biotechnology and Bioengineering, 111(3), 441–453.
31. Gao, C., Deng, Y., Feng, P., Mao, Z., Li, P., Yang, B., ... & Shuai, C. (2016). Current progress in bioactive ceramic scaffolds for bone repair and regeneration. International Journal of Molecular Sciences, 15(3), 4714–4732.
32. Gérard, C., Bordeleau, L. J., Barralet, J., & Doillon, C. J. (2010). The stimulation of angiogenesis and collagen deposition by copper. Biomaterials, 31(5), 824–831.
33. Grayson, W. L., Martens, T. P., Eng, G. M., Radisic, M., & Vunjak-Novakovic, G. (2008). Biomimetic approach to tissue engineering. Seminars in Cell & Developmental Biology, 20(6), 665–673.
34. Hajipour, M. J., Fromm, K. M., Akbar Ashkarran, A., Jimenez de Aberasturi, D., de Larramendi, I. R., Rojo, T., ... & Mahmoudi, M. (2012). Antibacterial properties of nanoparticles. Trends in Biotechnology, 30(10), 499–511.
35. Hanawa, T. (2020). Zirconia versus titanium in dentistry: A review. Dental Materials Journal, 39, 24–36. https://doi.org/10.4012/dmj.2019-172
36. Harris, L. D., Kim, B. S., & Mooney, D. J. (1998). Open pore biodegradable matrices formed with gas foaming. Journal of Biomedical Materials Research, 42(3), 396–402.
37. Hartgerink, J. D., Beniash, E., & Stupp, S. I. (2001). Self-assembly and mineralization of peptide-amphiphile nanofibers. *Science*, 294(5547), 1684–1688.
38. Heller, C., Schwentenwein, M., Russmueller, G., Varga, F., Stampfl, J., & Liska, R. (2009). Vinyl esters: Low cytotoxicity monomers for the fabrication of biocompatible 3D scaffolds by lithography based additive manufacturing. Journal of Polymer Science Part A: Polymer Chemistry, 47(24), 6941–6954.

39. Hench, L. L. (2006). The story of Bioglass. Journal of Materials Science: Materials in Medicine, 17(11), 967–978.
40. Hollister, S. J. (2005). Porous scaffold design for tissue engineering. *Nature Materials*, 4(7), 518–524.
41. Holy, C. E., Dang, S. M., Davies, J. E., & Shoichet, M. S. (2000). In vitro degradation of a novel poly(lactide-co-glycolide) 75/25 foam. Biomaterials, 20(13), 1177–1185.
42. Hu, C. M. J., Zhang, L., Aryal, S., Cheung, C., Fang, R. H., & Zhang, L. (2011). Erythrocyte membrane-camouflaged polymeric nanoparticles as a biomimetic delivery platform. Proceedings of the National Academy of Sciences, 108(27), 10980–10985.
43. Huang, X., El-Sayed, I. H., Qian, W., & El-Sayed, M. A. (2010). Cancer cell imaging and photothermal therapy in the near-infrared region by using gold nanorods. Journal of the American Chemical Society, 128(6), 2115–2120.
44. Huang, Z., Pei, N., Wang, Y., Xie, X., Sun, A., Shen, L., ... & Ge, J. (2015). Deep magnetic capture of magnetically loaded cells for spatially targeted therapeutics. Biomaterials, 31(8), 2130–2140.
45. Huebsch, N., & Mooney, D. J. (2009). Inspiration and application in the evolution of biomaterials. Nature, 462(7272), 426–432.
46. Hutmacher, D. W. (2000). Scaffolds in tissue engineering bone and cartilage. *Biomaterials*, 21(24), 2529–2543.
47. Jayakumar, R., Prabaharan, M., Kumar, P. S., Nair, S. V., & Tamura, H. (2011). Biomaterials based on chitin and chitosan in wound dressing applications. Biotechnology Advances, 29(3), 322–337.
48. Ji, W., Sun, Y., Yang, F., van den Beucken, J. J., Fan, M., Chen, Z., & Jansen, J. A. (2011). Bioactive electrospun scaffolds delivering growth factors and genes for tissue engineering applications. Pharmaceutical Research, 28(6), 1259–1272.
49. Kam, N. W. S., Jan, E., & Kotov, N. A. (2009). Electrical stimulation of neural stem cells mediated by humanized carbon nanotube composite made with extracellular matrix protein. Nano Letters, 9(1), 273–278.
50. Karageorgiou, V., & Kaplan, D. (2005). Porosity of 3D biomaterial scaffolds and osteogenesis. *Biomaterials*, 26(27), 5474–5491.
51. Kaur, G., Kumar, V., Baino, F., Mauro, J. C., Pickrell, G., Evans, I., & Bretcanu, O. (2019). Mechanical properties of bioactive glasses, ceramics, glass-ceramics, and composites: State-of-the-art review and future challenges. Materials Science and Engineering C: Materials for Biological Applications, 104, 109895. https://doi.org/10.1016/j.msec.2019.109895
52. Kelly, B. E., Bhattacharya, I., Heidari, H., Shusteff, M., Spadaccini, C. M., & Taylor, H. K. (2019). Volumetric additive manufacturing via tomographic reconstruction. Science, 363(6431), 1075–1079.
53. Khademhosseini, A., & Langer, R. (2016). A decade of progress in tissue engineering. Nature Protocols, 11(10), 1775–1781.
54. Kim, K. O., Lee, Y., Hwang, J. W., Kim, H., Kim, S. M., Chang, S. W., Lee, H. S., & Choi, Y. S. (2014). Wound healing properties of a 3-D scaffold comprising soluble silkworm gland hydrolysate and human collagen. Colloids and Surfaces B: Biointerfaces, 116, 318–326.
55. Kumar, A., & Jacob, A. (2022). Techniques in scaffold fabrication process for tissue engineering applications: A review. Journal of Applied Biology and Biotechnology, 10(3), 1–7
56. Langer, R., & Tirrell, D. A. (2004). Designing materials for biology and medicine. Nature, 428(6982), 487–492.
57. Langer, R., & Vacanti, J. P. (1993). Tissue engineering. *Science*, 260(5110), 920–926.

58. Laurent, S., Forge, D., Port, M., Roch, A., Robic, C., Vander Elst, L., & Muller, R. N. (2008). Magnetic iron oxide nanoparticles: Synthesis, stabilization, vectorization, physicochemical characterizations, and biological applications. Chemical Reviews, 108(6), 2064–2110.
59. Lauria, I., Kramer, M., Schröder, T., Kant, S., Hausmann, A., Böke, F., Leube, R., Telle, R., & Fischer, H. (2016). Inkjet printed periodical micropatterns made of inert alumina ceramics induce contact guidance and stimulate osteogenic differentiation of mesenchymal stromal cells. Acta Biomaterialia, 44, 85–96. https://doi.org/10.1016/j.actbio.2016.08.004
60. Lee, K. Y., & Mooney, D. J. (2001). Hydrogels for tissue engineering. Chemical Reviews, 101(7), 1869–1879.
61. Lener, T., Gimona, M., Aigner, L., Börger, V., Buzas, E., Camussi, G., ... & Giebel, B. (2015). Applying extracellular vesicles-based therapeutics in clinical trials. Journal of Extracellular Vesicles, 4(1), 30087.
62. Li, Z., Xie, M. B., Li, Y., Ma, Y., Li, J. S., & Dai, F. Y. (2016). Recent progress in tissue engineering and regenerative medicine. Journal of Biomaterials and Tissue Engineering, 6(10), 755–766.
63. Lutolf, M. P., & Hubbell, J. A. (2005). Synthetic biomaterials as instructive extracellular microenvironments for morphogenesis in tissue engineering. Nature Biotechnology, 23(1), 47–55.
64. Ma, P. X. (2008). Biomimetic materials for tissue engineering. *Advanced Drug Delivery Reviews*, 60(2), 184–198.
65. Maciel, P. P., Pessoa, J. A. M., de Medeiros, E. L. G., Batista, A. U. D., Fernandes Figueiredo, L. R., de Medeiros, E. S., de Oliveira Duarte, D. F., & Alves, A. F. (2020). Use of strontium doping glass-ceramic material for bone regeneration in critical defect: In vitro and in vivo analyses. Ceramics International, 46, 24940–24954. https://doi.org/10.1016/j.ceramint.2020.06.280
66. Mahdy, E. A., Sahbal, K. M., Mabrouk, M., Beherei, H. H., & Abdel-Monem, Y. K. (2021). Enhancement of glass-ceramic performance by TiO_2 doping: In vitro cell viability, proliferation, and differentiation. Ceramics International, 47, 6251–6261. https://doi.org/10.1016/j.ceramint.2020.10.203
67. Mao, A. S., & Mooney, D. J. (2015). Regenerative medicine: Current therapies and future directions. Proceedings of the National Academy of Sciences, 112(47), 14452–14459.
68. Martins, P., Gonçalves, A. C., Lanceros-Mendez, S., & Bhattacharya, A. (2013). Electroactive phases of poly(vinylidene fluoride): Determination, processing and applications. Progress in Polymer Science, 39(4), 683–706.
69. Monopoli, M. P., Åberg, C., Salvati, A., & Dawson, K. A. (2012). Biomolecular coronas provide the biological identity of nanosized materials. Nature Nanotechnology, 7(12), 779–786.
70. Murphy, S. V., & Atala, A. (2014). 3D bioprinting of tissues and organs. *Nature Biotechnology*, 32(8), 773–785.
71. Mussano, F., Genova, T., Serra, F., Carossa, M., Munaron, L., & Carossa, S. (2018). Nano-pore size of alumina affects osteoblastic response. International Journal of Molecular Sciences, 19(2), 528. https://doi.org/10.3390/ijms19020528
72. Nair, L. S., & Laurencin, C. T. (2007). Biodegradable polymers as biomaterials. Progress in Polymer Science, 32(8–9), 762–798.
73. Nair, M., Nancy, D., Krishnan, A. G., Anjusree, G. S., Vadukumpully, S., & Nair, S. V. (2013). Graphene oxide nanoflakes incorporated gelatin–hydroxyapatite scaffolds enhance osteogenic differentiation of human mesenchymal stem cells. Nanotechnology, 26(16), 161001.
74. Nel, A. E., Mädler, L., Velegol, D., Xia, T., Hoek, E. M. V., Somasundaran, P., ... & Thompson, M. (2009). Understanding biophysicochemical interactions at the nano–bio interface. *Nature Materials*, 8(7), 543–557.

75. Nel, A., Xia, T., Mädler, L., & Li, N. (2006). Toxic potential of materials at the nanolevel. Science, 311(5761), 622–627.
76. Nommeots-Nomm, A., Lee, P. D., & Jones, J. R. (2018). Direct ink writing of highly bioactive glasses. Journal of the European Ceramic Society, 38, 837–844. https://doi.org/10.1016/j.jeurceramsoc.2017.08.006
77. Noor, N., Shapira, A., Edri, R., Gal, I., Wertheim, L., & Dvir, T. (2019). 3D printing of personalized thick and perfusable cardiac patches and hearts. Advanced Science, 6(11), 1900344.
78. Novosel, E. C., Kleinhans, C., & Kluger, P. J. (2011). Vascularization is the key challenge in tissue engineering. Advanced Drug Delivery Reviews, 63(4–5), 300–311.
79. O'Brien, F. J. (2011). Biomaterials and scaffolds for tissue repair and regeneration. *Materials Today*, 14(3), 88–95.
80. Ozbolat, I. T., & Yu, Y. (2013). Bioprinting toward organ fabrication: Challenges and future trends. IEEE Transactions on Biomedical Engineering, 60(3), 691–699.
81. Pannier, A. K., & Shea, L. D. (2004). Controlled release systems for DNA delivery. Molecular Therapy, 10(1), 19–26.
82. Panyam, J., & Labhasetwar, V. (2003). Biodegradable nanoparticles for drug and gene delivery to cells and tissue. Advanced Drug Delivery Reviews, 55(3), 329–347.
83. Park, S. Y., Park, J., Sim, S. H., Sung, M. G., Kim, K. S., Hong, B. H., & Hong, S. (2011). Enhanced differentiation of human neural stem cells into neurons on graphene. Advanced Materials, 23(36), H263–H267.
84. Pham, Q. P., Sharma, U., & Mikos, A. G. (2006). Electrospinning of polymeric nanofibers for tissue engineering applications: A review. Tissue Engineering, 12(5), 1197–1211.
85. Pittenger, M. F., Mackay, A. M., Beck, S. C., Jaiswal, R. K., Douglas, R., Mosca, J. D., ... & Marshak, D. R. (1999). Multilineage potential of adult human mesenchymal stem cells. *Science*, 284(5411), 143–147.
86. Place, E. S., Evans, N. D., & Stevens, M. M. (2009). Complexity in biomaterials for tissue engineering. *Nature Materials*, 8(6), 457–470.
87. Poland, C. A., Duffin, R., Kinloch, I., Maynard, A., Wallace, W. A. H., Seaton, A., ... & Donaldson, K. (2008). Carbon nanotubes introduced into the abdominal cavity of mice show asbestos-like pathogenicity in a pilot study. Nature Nanotechnology, 3(7), 423–428.
88. Qi, X., Wang, H., Zhang, Y., Pang, L., Xiao, W., Jia, W., Zhao, S., Wang, D., Huang, W., & Wang, Q. (2018). Mesoporous bioactive glass-coated 3D printed borosilicate bioactive glass scaffolds for improving repair of bone defects. International Journal of Biological Sciences, 14, 471–484. https://doi.org/10.7150/ijbs.23872
89. Qiu, Q. Q., Leamy, P., Brittingham, J., Pomerleau, J., Kabaria, N., & Connor, J. (2009). Inactivation of bacterial spores and viruses in biological material using supercritical carbon dioxide with sterilant. Journal of Biomedical Materials Research Part B, 91(2), 572–578.
90. Ranga, N., Ranga, R., & Kumar, V. (2022). *BIOCERAMICS FOR TISSUE ENGINEERING APPLICATIONS* (pp. 146–154). https://doi.org/10.58532/V2BS14P2CH5
91. Raucci, M. G., Guarino, V., & Ambrosio, L. (2010). Hybrid composite scaffolds prepared by sol–gel method for bone regeneration. Composites Science and Technology, 70(13), 1861–1868.
92. Rezwan, K., Chen, Q. Z., Blaker, J. J., & Boccaccini, A. R. (2006). Biodegradable and bioactive porous polymer/inorganic composite scaffolds for bone tissue engineering. Biomaterials, 27(18), 3413–3431.
93. Richardson, T. P., Peters, M. C., Ennett, A. B., & Mooney, D. J. (2001). Polymeric system for dual growth factor delivery. Nature Biotechnology, 19(11), 1029–1034.
94. Riess, J. G. (2001). Oxygen carriers ("blood substitutes") — raison d'etre, chemistry, and some physiology. Chemical Reviews, 101(9), 2797–2920.

95. Roseti, L., Parisi, V., Petretta, M., Cavallo, C., Desando, G., Bartolotti, I., & Grigolo, B. (2017). Scaffolds for bone tissue engineering: State of the art and new perspectives. Materials Science and Engineering C, 78, 1246–1262.
96. Rouwkema, J., Rivron, N. C., & van Blitterswijk, C. A. (2008). Vascularization in tissue engineering. *Trends in Biotechnology*, 26(8), 434–441.
97. Sachs, E., Cima, M., & Cornie, J. (1990). Three-dimensional printing: Rapid tooling and prototypes directly from a CAD model. CIRP Annals, 39(1), 201–204.
98. Schmaljohann, D. (2006). Thermo- and pH-responsive polymers in drug delivery. Advanced Drug Delivery Reviews, 58(15), 1655–1670.
99. Seol, Y. J., Kang, H. W., Lee, S. J., Atala, A., & Yoo, J. J. (2014). Bioprinting technology and its applications. European Journal of Cardio-Thoracic Surgery, 46(3), 342–348.
100. Shea, L. D., Smiley, E., Bonadio, J., & Mooney, D. J. (1999). DNA delivery from polymer matrices for tissue engineering. Nature Biotechnology, 17(6), 551–554.
101. Shi, J., Votruba, A. R., Farokhzad, O. C., & Langer, R. (2010). Nanotechnology in drug delivery and tissue engineering: From discovery to applications. *Nano Letters*, 10(9), 3223–3230.
102. Shin, S. R., Jung, S. M., Zalabany, M., Kim, K., Zorlutuna, P., Kim, S. B., ... & Khademhosseini, A. (2013). Carbon-nanotube-embedded hydrogel sheets for engineering cardiac constructs and bioactuators. ACS Nano, 7(3), 2369–2380.
103. Shor, L., Güçeri, S., Chang, R., Gordon, J., Kang, Q., Hartsock, L., An, Y., & Sun, W. (2009). Precision extruding deposition (PED) fabrication of polycaprolactone (PCL) scaffolds for bone tissue engineering. Biofabrication, 1(1), 015003.
104. Stevens, M. M., & George, J. H. (2005). Exploring and engineering the cell surface interface. Science, 310(5751), 1135–1138.
105. Stuart, M. A. C., Huck, W. T. S., Genzer, J., Müller, M., Ober, C., Stamm, M., ... & Winnik, F. (2010). Emerging applications of stimuli-responsive polymer materials. Nature Materials, 9(2), 101–113.
106. Suamte, L., Tirkey, A., Barman, J., & Jayasekhar Babu, P. (2023). Various manufacturing methods and ideal properties of scaffolds for tissue engineering applications. *Smart Materials in Manufacturing*, *1*, 100011. https://doi.org/10.1016/j.smmf.2022.100011
107. Subia, B., Kundu, J., & Kundu, S. C. (2010). Biomaterial scaffold fabrication techniques for potential tissue engineering applications. Tissue Engineering, 141, 13–18.
108. Sun, M., Liu, A., Shao, H., Yang, X., Ma, C., Yan, S., Liu, Y., He, Y., & Gou, Z. (2016). Systematical evaluation of mechanically strong 3D printed diluted magnesium doping wollastonite scaffolds on osteogenic capacity in rabbit calvarial defects. Scientific Reports, 6(1), 34029. https://doi.org/10.1038/srep34029
109. Takahashi, K., & Yamanaka, S. (2006). Induction of pluripotent stem cells from mouse embryonic and adult fibroblast cultures by defined factors. *Cell*, 126(4), 663–676.
110. Thavornyutikarn, B., Chantarapanich, N., Sitthiseripratip, K., Thouas, G. A., & Chen, Q. (2014). Bone tissue engineering scaffolding: Computer-aided scaffolding techniques. Progress in Biomaterials, 3(2), 61–102.
111. Treacy, M. M. J., Ebbesen, T. W., & Gibson, J. M. (1996). Exceptionally high Young's modulus observed for individual carbon nanotubes. Nature, 381(6584), 678–680.
112. Valencia, P. M., Farokhzad, O. C., Karnik, R., & Langer, R. (2012). Microfluidic technologies for accelerating the clinical translation of nanoparticles. Nature Nanotechnology, 7(10), 623–629.
113. Venditto, V. J., & Szoka, F. C. (2013). Cancer nanomedicines: So many papers and so few drugs! Advanced Drug Delivery Reviews, 65(1), 80–88.

114. Ward, C. L., Corona, B. T., Yoo, J. J., Harrison, B. S., & Christ, G. J. (2013). Oxygen generating biomaterials preserve skeletal muscle homeostasis under hypoxic and ischemic conditions. PLOS ONE, 8(8), e72485.
115. Webster, T. J., Ergun, C., Doremus, R. H., Siegel, R. W., & Bizios, R. (2000). Enhanced functions of osteoblasts on nanophase ceramics. Biomaterials, 21(17), 1803–1810
116. Whitesides, G. M. (2003). The 'right' size in nanobiotechnology. *Nature Biotechnology*, 21(10), 1161–1165.
117. Williams, D. F. (2019). Challenges with the development of biomaterials for sustainable tissue engineering. Frontiers in Bioengineering and Biotechnology, 7, 127.
118. X. Du, S. Fu, Y. Zhu. 3D printing of ceramic-based scaffolds for bone tissue engineering: an overview. Journal of Materials Chemistry B, 2018.
119. Yeo, T., Ko, Y.-G., Kim, E. J., Kwon, O. K., Chung, H. Y., & Kwon, O. H. (2020). Promoting bone regeneration by 3D-printed poly (glycolic acid)/hydroxyapatite composite scaffolds. Journal of Industrial and Engineering Chemistry, 94, 343–351.
120. Zhang, Y., & Lawn, B. R. (2018). Novel zirconia materials in dentistry. Journal of Dental Research, 97, 140–147. https://doi.org/10.1177/0022034517737483

List of Publications

1. Conference Paper

Asiya Perween, Nishika Sharma and Prakash Chandra, “Review: Nanoparticle Applications in Scaffold-Based Tissue Engineering,” presented at the International Conference on Bioinformatics Applications in Biomedical Innovations (ICBABI-26) organized by the National Institute for Engineering and Research (NIER), Coimbatore, India, on 16th May 2026.

2. Poster Presentation

Asiya Perween, “Lipid Nanoparticles as Key Delivery Vehicles for mRNA Vaccines,” Biodiverse Poster Presentation, held on 28th April 2026 and presented scientific contributions related to biotechnology and biomedical.

Google Scholar

CERTIFICATE

OF PRESENTATION

NIER

International Conference on Bioinformatics Applications in Biomedical Innovations

(ICBABI-26)

16th May 2026 | Coimbatore - India

This is to certify that..... Asiya Perween .....affiliated with

..... Delhi Technological University, New Delhi, India .....has presented a paper titled

..... Review - Nanoparticle Applications in Scaffold - Based Tissue Engineering .....

.....

at the conference organized by the National Institute For Engineering And Research (NIER) held on

16th May 2026 at Coimbatore - India.

OPEN ACCESS

Dr. Tara Srivastava
Director, NIER

NIER

Raj Kumar
Co-ordinator, NIER

DOAJ DIRECTORY OF OPEN ACCESS JOURNALS

Bioeduverse
CERTIFICATE
OF PARTICIPATION
PROUDLY PRESENTED TO
This is to certify that Asiya Perween
has participated actively in the
BIOEDUVERSE POSTER PRESENTATION
held on 28/04/2026.
We appreciate their enthusiasm, effort and valuable contribution.
We wish them all the best for their future endeavors.
DATE
28/04/2026
COORDINATOR
BIOEDUVERSE

DELHI TECHNOLOGICAL UNIVERSITY

(Formerly Delhi College of Engineering)
Shahbad Daulatpur, Bawana Road, Delhi-110042

PLAGIARISM VERIFICATION

Title of the thesis "Nanoparticles in Scaffold Tissue Engineering: Design, Functionality, and Biomedical Applications"

Total pages: 69

Name of the Scholar: Asiya Perween (24\MSCBIO\62)

Supervisor: Prof. Prakash Chandra, Department of Biotechnology

This is to report that the above thesis was scanned for similarity detection.

Process and outcome are given below:

Software used : Turnitin

Similarity index: 5%

Total word count :17883

Date: 27/05/2026

Candidate's signatures

Supervisor Signature



turnitin Page 2 of 70 - Integrity Overview Submission ID trn:oid:::3618:137204817

5% Overall Similarity

The combined total of all matches, including overlapping sources, for each database.

Filtered from the Report

- Bibliography
- Quoted Text

Match Groups

18 Not Cited or Quoted 5%
Matches with neither in-text citation nor quotation marks

0 Missing Quotations 0%
Matches that are still very similar to source material

0 Missing Citation 0%
Matches that have quotation marks, but no in-text citation

0 Cited and Quoted 0%
Matches with in-text citation present, but no quotation marks

Top Sources

3% Internet sources
4% Publications
0% Submitted works (Student Papers)

Integrity Flags

0 Integrity Flags for Review

Our system's algorithms look deeply at a document for any inconsistencies that would set it apart from a normal submission. If we notice something strange, we flag it for you to review.

A Flag is not necessarily an indicator of a problem. However, we'd recommend you focus your attention there for further review.

Asiya perween

Contact

9934012084
asiyaperween01@gmail.com
Neyveli, Tamil Nadu

HOBBIES

- READING BOOKS
- SPORTS
- MUSIC
- COOKING

SOFT SKILLS

COMMUNICATION SKILL

TEAMWORK AND COLLABORATION

TIME MANAGEMENT

SOCIAL MEDIA

ANALYTICAL THINKIING

Languages

ENGLISH

HINDI

URDU

ABOUT ME

Motivated MSc Biotechnology student with a strong foundation in immunology, genetics, and molecular biology. Skilled in bioinformatics and molecular docking with hands-on training in drug discovery and computational biology. Passionate about research and innovation in life sciences, seeking an opportunity to contribute to a dynamic organization and enhance practical and analytical skills.

EDUCATION

- M.Sc Biotechnology Degree Pursuing from Delhi Technological University (2023-2026).
- B.Sc Biotechnology Degree completed from P.K. Roy Memorial College, Dhanbad (2020-2023).
- HSCC from Rajkamal Saraswati Vidya Mandir, Dhanbad (2019).
- SSLC from Dhanbad City School ,Dhanbad (2017) .

CERTIFICATION

- CERTIFICATE OF PARTICIPATION STEP-IN 2026: SCAFFOLD IN TISSUE ENGINEERING PLATFORMS, INNOVATIONS & POLICY ORGANIZED BY INDIAN INSTITUTE OF TECHNOLOGY KHARAGPUR FEBRUARY 23–24, 2026.
- DRUG DISCOVERY & MOLECULAR DOCKING TRAINING & INTERNSHIP (IIT MADRAS – MECHANICA 2025).
- BIOINFORMATICS & MOLECULAR DOCKING WORKSHOP (BIOSOC DTU)

COMPUTER SKILLS

- MS Office (Word, Excel, PowerPoint)
- Bioinformatics (BLAST, sequence analysis – basic)
- Molecular Docking (basic knowledge)
- Scientific Research & Data Analysis